

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
9 December 2004 (09.12.2004)

PCT


(10) International Publication Number  
**WO 2004/105910 A2**

- (51) International Patent Classification<sup>7</sup>: **B01D**
- (21) International Application Number: PCT/US2004/013721
- (22) International Filing Date: 3 May 2004 (03.05.2004)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:  
60/474,068 28 May 2003 (28.05.2003) US
- (71) Applicant (for all designated States except US): **WATERS INVESTMENTS LIMITED** [US/US]; 109 Lukens Drive, New Castle, DE 19720 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **O'GARA, John, E.** [US/US]; 30 Bellview Heights, Ashland, MA 01721 (US). **DING, Julia** [CN/US]; 5790 Highland Way #204, Middleton, WI 53562 (US). **WALSH, Daniel** [US/US]; 9 Brookside Avenue, Danvers, MA 01923 (US).
- (74) Agents: **LAURO, Peter, C. et al.**; Edwards & Angell, L.L.P., P.O. Box 55874, Boston, MA 02205 (US).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, B-Y; KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

[Continued on next page]

(54) Title: NOVEL NANOCOMPOSITES AND THEIR APPLICATION AS MONOLITH COLUMNS

**Schematic Description of Monoliths Made by Polymerization Sol-Gel Reactions.**



(57) Abstract: Novel materials for chromatographic separations, processes for their preparation, and separation devices containing the chromatographic materials. In particular, hybrid inorganic/organic monolith materials comprising a polymerized scaffolding nanocomposite (PSN), wherein the nanocomposite contains a scaffolding functionality capable of chemically interacting with a surface of a second material are described. The hybrid inorganic/organic materials have enhanced wall adhesion and increased resistance to shrinkage as compared to prior art monolith materials. The improved adhesion of the monoliths enable the preparation of capillary columns with an internal diameter (I.D.)  $\geq 50\mu m$ .

BEST AVAILABLE COPY

WO 2004/105910 A2

IAP16 RECEIVED 28 NOV 2005

## NOVEL NANOCOMPOSITES AND THEIR APPLICATION AS MONOLITH COLUMNS

### Related Application

- 5           This application claims the benefit of U.S. provisional patent application Ser. No. 60/474,068 filed May 28, 2003, the disclosure of which application is incorporated herein in its entirety by this reference.

### Background of the Invention

- 10           Packing materials for liquid chromatography (LC) are generally classified into two types: organic materials, *e.g.*, polydivinylbenzene; and inorganic materials typified by silica. Many organic materials are chemically stable against strongly alkaline and strongly acidic mobile phases, allowing flexibility in the choice of mobile phase pH. However, organic chromatographic materials generally result in columns with low efficiency, leading to inadequate separation performance, particularly with low
- 15           molecular-weight analytes. Furthermore, many organic chromatographic materials shrink and swell when the composition of the mobile phase is changed. In addition, most organic chromatographic materials do not have the mechanical strength of typical chromatographic silicas.

- 20           Due in large part to these limitations, silica is the material most widely used in High Performance Liquid Chromatography (HPLC). The most common applications employ silica that has been surface-derivatized with an organic group such as octadecyl (C<sub>18</sub>), octyl (C<sub>8</sub>), phenyl, amino, cyano, *etc.* As stationary phases for HPLC, these packing materials result in columns that have high efficiency and do not show evidence of shrinking or swelling.

- 25           However, a further problem associated with silica particles and polymer particles is packed bed stability. Chromatography columns packed with spherical particles can be considered to be random close packed lattices in which the interstices between the particles form a continuous network from the column inlet to the column outlet. This network forms the interstitial volume of the packed bed, and acts as a conduit for fluid to
- 30           flow through the packed column. In order to achieve maximum packed bed stability, the particles must be tightly packed, and hence, the interstitial volume is limited in the column. As a result, such tightly packed columns afford high column backpressures that are not desirable. Moreover, bed stability problems for these chromatography columns are still typically observed because of particle rearrangements.

A trend in current HPLC development is the miniaturization of column diameters that is driven by the often limited amount of samples originating from such areas as the life sciences. For mini- and microbore columns as well as capillary columns, the trade-off between particle size and backpressure becomes even more pronounced. For example, MacNair *et al.*<sup>(1)</sup> required specifically designed hardware that enabled an operating pressure as high as 500 MPa in order to achieve a HPLC separation of a tryptic digest in a 25cm long capillary column packed with 1  $\mu\text{m}$  silica particles. The pressure is one order of magnitude higher than the typical 40 MPa limitation of a commercial HPLC system.

In an attempt to overcome the combined problems of packed bed stability and high efficiency separations at low backpressures and high flow rates, several groups have reported the use of monolith materials in chromatographic separations. Monolith materials are characterized by a continuous, interconnected pore structure of large macropores, the size of which can be changed independent of the skeleton size without causing bed instability. The presence of large macropores allows liquid to flow directly through with very little resistance resulting in very low backpressures even at high flow rates.

Monolith columns have been designed to disobey the trade-off rule associated with packed particle beds. Theoretically, they can exhibit combined properties of low backpressure and high efficiency that go beyond the limits of packed particle columns in pressure-driven liquid chromatography. Capillary monolith columns comprising polymeric, inorganic silica and organic-inorganic hybrid materials have been studied and reported in the literature.<sup>(2, 3)</sup> The polymeric monoliths are made primarily *via* a radical polymerization of methacrylate or styrene-divinylbenzene(DVB) monomers and are used under electroosmotic flow in electrochromatography applications and low pressure pump driven applications because of their limited mechanical strength under high pressure.

Silica monoliths have also been applied in HPLC separations by Nakanishi *et al.*<sup>(3)</sup> and have demonstrated an efficiency similar to 5 $\mu\text{m}$  particles but with permeability 25-30 times higher. However, due to the shrinkage of the silica skeleton, silica capillaries with an I.D. larger than 50  $\mu\text{m}$  showed much lower efficiency, and in all cases 5-15% of the length of each capillary end had to be cut off to remove large voids caused by shrinkage that formed between the monolith and capillary wall before the capillary could be used.

In another publication, Nakanishi *et al.*<sup>(4)</sup> demonstrated the possibility of making a capillary column of 200 $\mu\text{m}$  internal diameter (I.D.) from a mixture of tetramethoxysilane and methyltrimethoxysilane. However, these hybrid-type silica monoliths capillaries still had large voids caused by shrinkage that formed between the

monolith and capillary wall and required cutting of 5-15% of the length of each capillary end before use. The hybrid-type silica monolith also had a three-fold increase in separation impedance versus the analogous silica monolith column of 50  $\mu\text{m}$  I.D.

5 Polymeric capillary monolith columns prepared by a UV polymerization of (3-methacryloxypropyl)trimethoxysilane were first reported by Zare *et al.* in 2001.<sup>(5)</sup> The elution order of the Zare column is similar to that of a reversed-phase column where larger molecular weight or more hydrophobic analytes elute later than the smaller molecular weight or more hydrophilic analytes, indicating that the polymerized methylacrylate groups are located on the surface of the monolith structure. Although 10 Zare's work has been successfully applied in electrochromatography, poor column efficiency, poor adhesion between the capillary wall and the monolith structure, and inhomogeneity of the monolith structure were observed in pressure driven separations.<sup>(6)</sup> Moreover, as a consequence of the utilization of photopolymerization rather than thermal polymerization, the polyimide coating of the glass capillary must be removed prior to 15 use. This unprotected fused silica tubing becomes very fragile and is easily broken. Therefore, only columns with a limited length can be prepared by this method.

Current monolith columns have significant shrinkage, resulting in poor wall adhesion, and consequently, only columns with an I.D. of less than 150  $\mu\text{m}$  have been prepared. Therefore, a need exists for novel materials that overcome the problems that 20 are associated with known materials. In particular, there is a need for monolith materials with increased resistance to shrinkage and enhanced wall adhesion that can be used to prepare chromatographic columns with an I.D. of 150  $\mu\text{m}$  and greater.

### Summary of the Invention

25 The present invention provides novel hybrid inorganic/organic materials and methods for their preparation. In particular, the invention provides nanocomposite monolith materials having increased resistance to shrinkage and novel physical characteristics. The nanocomposites of the invention have enhanced capillary wall adhesion as compared to prior art monolith materials. The improved adhesion of the 30 monoliths of the invention enables the preparation of capillary columns with an internal diameter (I.D.)  $\geq 150 \mu\text{m}$ .

Accordingly, in one aspect, the invention provides a hybrid inorganic/organic material comprising a polymerized scaffolding nanocomposite (PSN), wherein the nanocomposite contains a scaffolding functionality capable of chemically interacting 35 with a surface of a second material.

In another aspect, the invention provides a hybrid inorganic/organic monolith comprising a polymerized scaffolding nanocomposite (PSN), wherein the nanocomposite contains a scaffolding functionality capable of chemically interacting with a surface of a second material.

5        Additionally, the present invention provides a method of preparation of a hybrid inorganic/organic monolith comprising a polymerized scaffolding nanocomposite (PSN), wherein the nanocomposite contains a scaffolding functionality capable of chemically interacting with a surface of a second material, said method comprising the steps of

- a) forming a sol-gel by the reaction of two or more monomers;
  - 10        b) initiating a polymerization reaction; and
  - c) allowing the monomers to react through a polymerization sol-gel (PSG) reaction,
- thereby preparing the hybrid inorganic/organic monolith.

15        In a related aspect, the invention provides a method of preparation of a hybrid inorganic/organic monolith comprising a polymerized scaffolding nanocomposite (PSN), wherein the nanocomposite contains a scaffolding functionality capable of chemically interacting with a surface of a second material, said method comprising the steps of

- a) forming a sol-gel by the reaction of two or more monomers;
  - b) initiating a polymerization reaction;
  - 20        c) allowing the monomers to react through a polymerization sol-gel (PSG) reaction; and
  - d) modifying the pore structure of the material,
- thereby preparing the hybrid inorganic/organic monolith.

25        In yet another aspect, the invention provides a separations device comprising a) a surface capable of accepting a monolith material comprising a polymerized scaffolding nanocomposite (PSN) material, said surface comprising an anchoring functionality and

b) a hybrid inorganic/organic monolith comprising a polymerized scaffolding nanocomposite (PSN), wherein the nanocomposite contains a scaffolding  
30        functionality capable of chemically interacting with the anchoring functionality on said surface, and wherein said hybrid organic/inorganic monolith is anchored to said surface by a chemical interaction between said scaffolding functionality and anchoring functionality.

In a related aspect, the invention provides a fused-silica capillary column, comprising

- a) a fused-silica capillary column having a cylindrical interior surface capable of accepting a monolith comprising a polymerized scaffolding nanocomposite (PSN) material, said interior surface comprising an anchoring functionality, and
- b) a hybrid inorganic/organic monolith comprising a polymerized scaffolding nanocomposite (PSN), wherein the nanocomposite contains a scaffolding functionality capable of chemically interacting with the anchoring functionality on said surface, and wherein said hybrid organic/inorganic monolith is anchored to said surface by a chemical interaction between said scaffolding functionality and anchoring functionality.

Another aspect of the invention provides a method of *in situ* preparation of a hybrid inorganic/organic monolith in a fused-silica capillary column, said method comprising:

- forming an anchoring functionality on an interior surface of said capillary column; and

- forming inside said capillary column a hybrid inorganic/organic monolith comprising a polymerized scaffolding nanocomposite (PSN), wherein the nanocomposite contains a scaffolding functionality capable of chemically interacting with the anchoring functionality on said surface, said monolith being formed by:

- a) forming a sol-gel by the reaction of two or more monomers;
  - b) initiating a polymerization reaction; and
  - c) allowing the monomers to react through a polymerization sol-gel (PSG) reaction;
- whereby said scaffolding functionality and said anchoring functionality chemically interact to thereby anchor said monolith to said surface, such that a hybrid inorganic/organic monolith is prepared *in situ* in a fused-silica capillary column.

In another related aspect, the invention provides a method of *in situ* preparation of a hybrid inorganic/organic monolith in a fused-silica capillary column, said method comprising:

- forming an anchoring functionality on an interior surface of said capillary column; and

- forming inside said capillary column a hybrid inorganic/organic monolith comprising a polymerized scaffolding nanocomposite (PSN), wherein the

nanocomposite contains a scaffolding functionality capable of chemically interacting with the anchoring functionality on said surface, said monolith being formed by:

- a) forming a sol-gel by the reaction of two or more monomers;
- b) initiating a polymerization reaction;
- 5 c) allowing the monomers to react through a polymerization sol-gel (PSG) reaction; and
- d) modifying the pore structure of the monolith,

whereby said scaffolding functionality and said anchoring functionality chemically interact to thereby anchor said monolith to said surface, such that a hybrid  
10 inorganic/organic monolith is prepared *in situ* in a fused-silica capillary column.

Another aspect of the invention provides an inorganic/organic hybrid monolith comprising a scaffolding functionality capable of chemically interacting with a surface of a second material, produced by the process of

- a) forming a sol-gel by the reaction of two or more monomers;
- 15 b) initiating a polymerization reaction; and
- c) allowing the monomers to react through a polymerization sol-gel (PSG) reaction.

In a related aspect, the invention provides an inorganic/organic hybrid monolith comprising a scaffolding functionality capable of chemically interacting with a surface of  
20 a second material, produced by the process of

- a) forming a sol-gel by the reaction of two or more monomers;
- b) initiating a polymerization reaction;
- c) allowing the monomers to react through a polymerization sol-gel (PSG) reaction; and
- 25 d) modifying the pore structure of the monolith.

In yet another related aspect, the invention provides a method of preparation of a hybrid inorganic/organic material comprising a polymerized scaffolding nanocomposite (PSN), comprising the steps of

- a) forming a sol-gel by the reaction of two or more monomers;
- 30 b) initiating a polymerization reaction; and
- c) allowing the monomers to react through a polymerization sol-gel (PSG) reaction,

thereby preparing the hybrid inorganic/organic monolith, wherein the monolith contains a scaffolding functionality capable of chemically interacting with a surface of a second material.

5 In another aspect, the invention provides a method of preparation of a hybrid inorganic/organic material comprising a polymerized scaffolding nanocomposite (PSN), comprising the steps of

- a) forming a sol-gel by the reaction of two or more monomers;
- b) initiating a polymerization reaction;
- c) allowing the monomers to react through a polymerization sol-gel (PSG)
- 10 reaction; and
- d) modifying the pore structure of the material,

thereby preparing the hybrid inorganic/organic material, wherein the nanocomposite contains a scaffolding functionality capable of chemically interacting with a surface of a second material.

15 Yet another aspect of the invention provides a capillary column, wherein the interior surface of the capillary column is derivatized with a polymerizable anchoring functionality.

#### **Brief Description of Drawings**

20 *Figures 1A -1D* depict a schematic representation of monoliths made by the polymerization sol gel (PSG) reaction. Figure 1A depicts examples of hybrid and inorganic monomers in chemical structure and schematic form. Figure 1B is a schematic depiction of hybrid and inorganic monomer hydrolysis and oligomerization. Figure C is a simplified depiction of the PSG reaction to form a cross-sectional block of

25 polymerized scaffolding nanocomposite material. Figure D is a simplified cross-sectional view of the PSN material, including expanding views of the PSN material.

#### **Detailed Description of the Invention**

30 The present invention provides novel hybrid inorganic/organic materials, and methods for their preparation. In particular, the invention provides nanocomposite monolith materials having increased resistance to shrinkage and novel physical characteristics. The nanocomposites of the invention have enhanced capillary wall adhesion, as compared to prior art monolith materials. The improved adhesion of the



monoliths of the invention enables the preparation of capillary columns with an internal diameter (I.D.)  $\geq 150 \mu\text{m}$ .

In an advantageous embodiment, the invention provides novel, inorganic/organic monolith materials inside a fused silica capillary column. In accordance with this  
5 embodiment, the monoliths of the invention are prepared *in situ* inside a surface-modified fused silica capillary column through simultaneous organic polymerization and sol-gel reaction of a silane mixture that has an organosilane monomer containing at least one organic polymerizable group, such as, *e.g.*, (3-methacryloxypropyl)trimethoxysilane.

## 10 **Definitions**

These and other embodiments of the invention will be described with reference to following definitions that, for convenience, are collected here.

The term "alicyclic group" includes closed ring structures of three or more carbon atoms. Alicyclic groups include cycloparaffins or naphthenes that are saturated cyclic  
15 hydrocarbons, cycloolefins which are unsaturated with two or more double bonds, and cycloacetylenes which have a triple bond. They do not include aromatic groups. Examples of cycloparaffins include cyclopropane, cyclohexane, and cyclopentane. Examples of cycloolefins include cyclopentadiene and cyclooctatetraene. Alicyclic groups also include fused ring structures and substituted alicyclic groups such as alkyl  
20 substituted alicyclic groups. In the instance of the alicyclics such substituents can further comprise a lower alkyl, a lower alkenyl, a lower alkoxy, a lower alkylthio, a lower alkylamino, a lower alkylcarboxyl, a nitro, a hydroxyl,  $-\text{CF}_3$ ,  $-\text{CN}$ , or the like.

The term "aliphatic group" includes organic compounds characterized by straight or branched chains, typically having between 1 and 22 carbon atoms. Aliphatic groups  
25 include alkyl groups, alkenyl groups and alkynyl groups. In complex structures, the chains can be branched or cross-linked. Alkyl groups include saturated hydrocarbons having one or more carbon atoms, including straight-chain alkyl groups and branched-chain alkyl groups. Such hydrocarbon moieties may be substituted on one or more carbons with, for example, a halogen, a hydroxyl, a thiol, an amino, an alkoxy, an  
30 alkylcarboxy, an alkylthio, or a nitro group. Unless the number of carbons is otherwise specified, "lower aliphatic" as used herein means an aliphatic group, as defined above (*e.g.*, lower alkyl, lower alkenyl, lower alkynyl), but having from one to six carbon atoms. Representative of such lower aliphatic groups, *e.g.*, lower alkyl groups, are methyl, ethyl, n-propyl, isopropyl, 2-chloropropyl, n-butyl, sec-butyl, 2-aminobutyl,  
35 isobutyl, tert-butyl, 3-thiopentyl, and the like. As used herein, the term "nitro" means -

NO<sub>2</sub>; the term "halogen" designates -F, -Cl, -Br or -I; the term "thiol" means SH; and the term "hydroxyl" means -OH.

The terms "alkenyl" and "alkynyl" refer to unsaturated aliphatic groups analogous to alkyls, but which contain at least one double or triple bond respectively. Suitable  
5 alkenyl and alkynyl groups include groups having 2 to about 12 carbon atoms, preferably from 1 to about 6 carbon atoms.

The term "alkoxy" as used herein means an alkyl group, as defined herein, having an oxygen atom attached thereto. Representative alkoxy groups include groups having 1 to about 12 carbon atoms, preferably 1 to about 6 carbon atoms, *e.g.*, methoxy, ethoxy,  
10 propoxy, tert-butoxy and the like.

The term "alkyl" includes saturated aliphatic groups, including straight-chain alkyl groups, branched-chain alkyl groups, cycloalkyl (alicyclic) groups, alkyl substituted cycloalkyl groups, and cycloalkyl substituted alkyl groups. In certain embodiments, a straight chain or branched chain alkyl has 30 or fewer carbon atoms in its backbone, *e.g.*,  
15 C<sub>1</sub>-C<sub>30</sub> for straight chain or C<sub>3</sub>-C<sub>30</sub> for branched chain. In certain embodiments, a straight chain or branched chain alkyl has 20 or fewer carbon atoms in its backbone, *e.g.*, C<sub>1</sub>-C<sub>20</sub> for straight chain or C<sub>3</sub>-C<sub>20</sub> for branched chain, and more preferably 18 or fewer. Likewise, preferred cycloalkyls have from 4-10 carbon atoms in their ring structure, and more preferably have 4-7 carbon atoms in the ring structure. The term "lower alkyl"  
20 refers to alkyl groups having from 1 to 6 carbons in the chain, and to cycloalkyls having from 3 to 6 carbons in the ring structure.

Moreover, the term "alkyl" (including "lower alkyl") as used throughout the specification and claims includes both "unsubstituted alkyls" and "substituted alkyls", the latter of which refers to alkyl moieties having substituents replacing a hydrogen on  
25 one or more carbons of the hydrocarbon backbone. Such substituents can include, for example, halogen, hydroxyl, alkylcarbonyloxy, arylcarbonyloxy, alkoxycarbonyloxy, aryloxy, carboxylate, alkylcarbonyl, alkoxycarbonyl, aminocarbonyl, alkylthiocarbonyl, alkoxyl, phosphate, phosphonate, phosphinate, cyano, amino (including alkyl amino, dialkylamino, arylamino, diarylamino, and alkylarylamino),  
30 acylamino (including alkylcarbonylamino, arylcarbonylamino, carbamoyl and ureido), amidino, imino, sulfhydryl, alkylthio, arylthio, thiocarboxylate, sulfate, sulfonate, sulfamoyl, sulfonamido, nitro, trifluoromethyl, cyano, azido, heterocyclyl, aralkyl, or an aromatic or heteroaromatic moiety. It will be understood by those skilled in the art that the moieties substituted on the hydrocarbon chain can themselves be substituted, if  
35 appropriate. Cycloalkyls can be further substituted, *e.g.*, with the substituents described above. An "aralkyl" moiety is an alkyl substituted with an aryl, *e.g.*, having 1 to 3

separate or fused rings and from 6 to about 18 carbon ring atoms, *e.g.*, phenylmethyl (benzyl).

The term "alkylamino" as used herein means an alkyl group, as defined herein, having an amino group attached thereto. Exemplary alkylamino groups include groups  
5 having 1 to about 12 carbon atoms, preferably from 1 to about 6 carbon atoms.

The term "alkylthio" refers to an alkyl group, as defined herein, having a  
sulfhydryl group attached thereto. Exemplary alkylthio groups include groups having 1  
to about 12 carbon atoms, preferably from 1 to about 6 carbon atoms. The term  
"alkylcarboxyl" as used herein means an alkyl group, as defined above, having a  
10 carboxyl group attached thereto. The term "amino," as used herein, refers to an  
unsubstituted or substituted moiety of the formula  $-NR_aR_b$ , in which  $R_a$  and  $R_b$  are each  
independently hydrogen, alkyl, aryl, or heterocyclyl, or  $R_a$  and  $R_b$ , taken together with  
the nitrogen atom to which they are attached, form a cyclic moiety having from 3 to 8  
atoms in the ring. Thus, the term "amino" includes cyclic amino moieties such as  
15 piperidinyl or pyrrolidinyl groups, unless otherwise stated. An "amino-substituted amino  
group" refers to an amino group in which at least one of  $R_a$  and  $R_b$ , is further substituted  
with an amino group.

The language "anchoring functionality" is intended to include functional moieties  
that promote the ability of the second material to chemically interact with the PSN  
20 material. In certain embodiments, the anchoring functionality is a polymerizable group,  
including, but not limited to vinyl, acrylate, methacrylate, acrylamide, methacrylamide,  
styrene, divinylbenzene, itaconate, fumarate, alkyne, azo compounds, and combinations  
thereof.

The term "anchoring" refers to the act of adhesion of one material to a second  
25 material. The extent of adhesion is a direct result of the chemical interaction of the first  
material with the second material, and is intended to include a range of interactions  
which extend from flexible interactions to strict immobilization.

The term "aromatic group" includes unsaturated cyclic hydrocarbons containing  
one or more rings. Aromatic groups include 5- and 6-membered single-ring groups  
30 which may include from zero to four heteroatoms, for example, benzene, pyrrole, furan,  
thiophene, imidazole, oxazole, thiazole, triazole, pyrazole, pyridine, pyrazine, pyridazine  
and pyrimidine, and the like. The aromatic ring may be substituted at one or more ring  
positions with, for example, a halogen, a lower alkyl, a lower alkenyl, a lower alkoxy, a  
lower alkylthio, a lower alkylamino, a lower alkylcarboxyl, a nitro, a hydroxyl,  $-CF_3$ , -  
35 CN, or the like.

The term "aryl" includes 5- and 6-membered single-ring aromatic groups that may include from zero to four heteroatoms, for example, unsubstituted or substituted benzene, pyrrole, furan, thiophene, imidazole, oxazole, thiazole, triazole, pyrazole, pyridine, pyrazine, pyridazine and pyrimidine, and the like. Aryl groups also include polycyclic fused aromatic groups such as naphthyl, quinolyl, indolyl, and the like. The aromatic ring can be substituted at one or more ring positions with such substituents, e.g., as described above for alkyl groups. Suitable aryl groups include unsubstituted and substituted phenyl groups.

The term "aryloxy" as used herein means an aryl group, as defined above, having an oxygen atom attached thereto. The term "aralkoxy" as used herein means an aralkyl group, as defined above, having an oxygen atom attached thereto. Suitable aralkoxy groups have 1 to 3 separate or fused rings and from 6 to about 18 carbon ring atoms, e.g., O-benzyl.

The language "azo compounds" is intended to include azo containing groups as surface functionalities. These azo groups on the surface can initiate the polymerization from the surface into the bulk nanocomposite. This approach is achieved using silanes that contain azo groups in them and that can be bonded onto the walls of the glass capillaries.<sup>9,10</sup>

The language "chemical interaction" is intended to include, but is not limited to hydrophobic/hydrophilic, ionic (e.g., coulombic attraction/ repulsion, ion-dipole, charge-transfer), chemical bonding, Van der Waals, and hydrogen bonding. The term chemical interaction is meant to be distinguished from physical interactions, such as physical friction between surfaces.

The language "chemical bonding" is intended to include the formation of a covalent bond, e.g., organic covalent bond or inorganic covalent bond. Organic covalent bonds are defined to involve the formation of a covalent bond between the common elements of organic chemistry including but not limited to hydrogen, boron, carbon, nitrogen, oxygen, silicon, phosphorus, sulfur, and the halogens. In addition, carbon-silicon and carbon-oxygen-silicon bonds are defined as organic covalent bonds, whereas silicon-oxygen-silicon bonds that are not defined as organic covalent bonds, i.e., silicon-oxygen-silicon bonds are defined as inorganic covalent bonds.

The language "capillary column" refers to a chromatographic column with internal diameters (I.D.) in the range of 50-2000  $\mu\text{m}$ .

The terms "coalescing" and "coalesced," as used in the language "coalesced particles" are intended to describe a material in which several individual components have become coherent to result in one new component by an appropriate chemical or


physical process, *e.g.*, heating. The term coalesced is meant to be distinguished from a collection of individual particles in close physical proximity, *e.g.*, in a bed formation, in which the end product comprises individual particles.

5 The language "dense material" is intended to include hybrid materials, which upon view of an axial cross-section of the material's surface are comprised of the hybrid material and macropores with an average diameter of less than 0.5  $\mu\text{m}$  that separate the hybrid material.

10 The terms "derivatized" or "derivatization" are intended to include to the property or characteristic of anchoring or coating an agent of alternate functionality onto a second material by conversion of the functionality of the receiving surface of the second material to the alternate functionality, *e.g.*, by coating or chemical bonding, *e.g.*, polymerization.


15 The term "functionalizing group" includes organic groups which impart a certain chromatographic functionality to a chromatographic stationary phase, including, *e.g.*, octadecyl ( $\text{C}_{18}$ ) or phenyl. Such functionalizing groups are present in, for example, surface modifiers such as disclosed herein which are attached to the base material, *e.g.*, via derivatization or coating and later crosslinking, imparting the chemical character of the surface modifier to the base material. In one embodiment, such surface modifiers have the formula  $\text{Z}_a(\text{R}')_b\text{Si-R}$ , where  $\text{Z} = \text{Cl, Br, I, C}_1 - \text{C}_5$  alkoxy, dialkylamino or trifluoromethanesulfonate;  $a$  and  $b$  are each an integer from 0 to 3 provided that  $a + b =$   
20 3;  $\text{R}'$  is a  $\text{C}_1 - \text{C}_6$  straight, cyclic or branched alkyl group, and  $\text{R}$  is a functionalizing group.  $\text{R}'$  may be, *e.g.*, methyl, ethyl, propyl, isopropyl, butyl, *t*-butyl, *sec*-butyl, pentyl, isopentyl, hexyl or cyclohexyl; preferably,  $\text{R}'$  is methyl.

25 The functionalizing group  $\text{R}$  may include alkyl, alkenyl, alkynyl, aryl, cyano, amino, diol, nitro, ester, a cation or anion exchange group, embedded polar functionalities, or an alkyl or aryl group containing an embedded polar functionality. Examples of suitable  $\text{R}$  functionalizing groups include  $\text{C}_1 - \text{C}_{30}$  alkyl, including  $\text{C}_1 - \text{C}_{20}$ , such as octyl ( $\text{C}_8$ ), octadecyl ( $\text{C}_{18}$ ), and triacontyl ( $\text{C}_{30}$ ); alkaryl, *e.g.*,  $\text{C}_1 - \text{C}_4$ -phenyl; cyanoalkyl groups, *e.g.*, cyanopropyl; diol groups, *e.g.*, propyldiol; amino groups, *e.g.*,  
30 aminopropyl; and alkyl or aryl groups with embedded polar functionalities, *e.g.*, carbamate functionalities such as disclosed in U. S. Patent No. 5,374,755, the text of which is incorporated herein by reference. Such groups include those of the general formula



wherein  $l$ ,  $m$ ,  $o$ ,  $r$ , and  $s$  are 0 or 1,  $n$  is 0, 1, 2 or 3,  $p$  is 0, 1, 2, 3 or 4 and  $q$  is an integer from 0 to 19;  $R_3$  is selected from the group consisting of hydrogen, alkyl, cyano and phenyl; and  $Z$ ,  $R'$ ,  $a$  and  $b$  are defined as above. Preferably, the carbamate functionality

5 has the general structure indicated below:



wherein  $R^5$  may be, *e.g.*, cyanoalkyl, *t*-butyl, butyl, octyl, dodecyl, tetradecyl, octadecyl, or benzyl. Advantageously,  $R^5$  is octyl, dodecyl, or octadecyl.

The term "heterocyclic group" includes closed ring structures in which one or

10 more of the atoms in the ring is an element other than carbon, for example, nitrogen, sulfur, or oxygen. Heterocyclic groups can be saturated or unsaturated and heterocyclic groups such as pyrrole and furan can have aromatic character. They include fused ring structures such as quinoline and isoquinoline. Other examples of heterocyclic groups include pyridine and purine. Heterocyclic groups can also be substituted at one or more

15 constituent atoms with, for example, a halogen, a lower alkyl, a lower alkenyl, a lower alkoxy, a lower alkylthio, a lower alkylamino, a lower alkylcarboxyl, a nitro, a hydroxyl,  $-\text{CF}_3$ ,  $-\text{CN}$ , or the like. Suitable heteroaromatic and heteroalicyclic groups generally will have 1 to 3 separate or fused rings with 3 to about 8 members per ring and one or more

20 N, O or S atoms, *e.g.* coumarinyl, quinolinyl, pyridyl, pyrazinyl, pyrimidyl, furyl, pyrrolyl, thienyl, thiazolyl, oxazolyl, imidazolyl, indolyl, benzofuranyl, benzothiazolyl, tetrahydrofuranyl, tetrahydropyranyl, piperidinyl, morpholino and pyrrolidinyl.

The term "hybrid", *i.e.*, as used in the language "inorganic/organic hybrid material" or "inorganic/organic hybrid monolith" includes inorganic-based structures wherein an organic functionality is integral to both the internal or "skeletal" inorganic

25 structure. The inorganic portion of the hybrid material may be selected from, but are not

limited to alumina, silica, titanium oxide, zirconium oxide, and ceramic material. In one embodiment the inorganic portion of the hybrid material is silica.

The language "Hydrophile-Lipophile Balance (HLB)," is art recognized and is intended to characterize the solubility of surfactants. The number provides a guide to the skilled artisan in deciding which surfactant to use in a given emulsion. Surfactants with an HLB number of <10 (or depending on your reference, 3-6) have an affinity for oil over water, and as a result water droplets tend to form in an oil phase. The converse is true for surfactants with HLB numbers >10 (or 8-13), which have an affinity for water over oil, and as a result oil droplets tend to form in a water phase. In certain embodiments the HLB number typically ranges from 0 to about 15, but can go as high as 60. The HLB number may be derived by a variety of methods, providing a relative, rather than an exact value.

The term "material" as it is used herein, is intended to include three-dimensional copolymers that have been formed in a single piece. In one embodiment, the material of the invention is prepared by casting precursors into a mold of a desired shape. Materials of the invention include, but are not limited to polymeric materials such as monoliths or non-monolith materials, *e.g.*, particles, copolymers with low porosity, or porous copolymers that do not have interconnected pore structure.

The term "macropore" is intended to include pores of a material, or channels through the material, which allow liquid to flow directly through the material with reduced resistance at chromatographically-useful flow rates. For example, macropores of the present invention are intended to include, but are not limited to pores with a pore diameter larger than about 0.05  $\mu\text{m}$ , pores with a pore diameter ranging from about 0.1  $\mu\text{m}$  to about 10  $\mu\text{m}$ , pores with a pore diameter ranging from about 0.5  $\mu\text{m}$  to about 5  $\mu\text{m}$ , and pores with a pore diameter ranging from about 0.8  $\mu\text{m}$  to about 4  $\mu\text{m}$ . It should be understood that the selection of macropore size in the materials of the invention for use in chromatography may be analyzed based on, at least, column backpressure and efficiency. If the macropore size is too small, the column backpressure will become too great for chromatographic use, while if the macropore diameter is too large, the column will lose chromatographic efficiency.

The language "minimally water soluble," is intended to include the ability of the compound to remain at least soluble enough to allow the intended reaction to move forward. In certain embodiments, the language "minimally soluble" is intended to include a range of solubility between sparingly soluble and fully soluble. It should be understood that the solubility includes solubility induced by using, for example, heat or additional reagents. In certain embodiments, 2,2'-azobis(isobutyronitrile) would be understood by one skilled the art to be minimally water soluble.

The term "monolith" refers to a porous, three-dimensional material having a continuous interconnected pore structure in a single piece. The term monolith is meant to be distinguished from a collection of individual particles packed into a bed formation, in which the end product comprises individual particles. The term monolith is also meant to be distinguished from three-dimensional polymers with low porosity or porous three-dimensional polymers that do not have interconnected pore structure. In one embodiment, a monolith of the invention is prepared by casting precursors into a mold of a desired shape. In another embodiment, the monolith comprises coalesced particles. In yet another embodiment, the monolith material may be used for chromatography, *i.e.*, the monolith is a chromatographically useful material, *e.g.*, a chromatographic column.

The term "nanophase" refers to organic or inorganic phase aggregations that have formed based on phase separations at the molecular level. In particular embodiments of the invention, phase separation at the molecular level is generated upon the simultaneous reaction of hybrid and inorganic monomers through a polymerization sol-gel reaction. Figure 1 is a graphical depiction of the polymerization sol-gel reaction of the invention that leads to the production of organic and inorganic nanophases.

The language "polymerized scaffolding nanocomposite (PSN)" refers to hybrid composite materials that comprise a polymerized organic nanophase surrounded by an inorganic nanophase, *e.g.*, polymerized siloxane, wherein the nanophases form independently through independent reactions, *e.g.*, a polymerization and a sol gel reaction, and wherein the organic and inorganic nanophases interconnect by chemical bond formation through a hybrid monomer, *e.g.*, by condensation of the inorganic phase, *e.g.*, of the hybrid monomer to an inorganic monomer; and polymerization of the organic phase, *e.g.*, radical polymerization, such that a hybrid material forms with a plurality of surface scaffolding functionalities.

The language "polymerization sol-gel (PSG) reaction" refers to the approach of preparing hybrid materials using simultaneous polymerization reactions and sol-gel reactions, wherein the organic and inorganic nanophases interconnect by chemical bond formation through an interaction with a hybrid monomer, *e.g.*, by condensation of the inorganic phase, *e.g.*, of the hybrid monomer to an inorganic monomer; and polymerization of the organic phase, *e.g.*, radical polymerization, such that a hybrid material forms. In a particular embodiment, the materials are made from a mixture of a tetraalkoxysilane, *e.g.*, tetramethoxysilane, and a polymerizable organosilane, *e.g.*, (3-methacryloxypropyl)trimethoxysilane, wherein the organosilane is minimally water soluble, *e.g.*, sufficient to produce a polymerized scaffolding nanocomposite (*i.e.*, the polymerizable group will have an affect on this solubility). For example, the starting



silanes have limited solubility in water. As the SiOR bonds are hydrolyzed to SiOH, the SiOH monomer that forms is substantially soluble in water.

The term "polymerization" refers to any process that results from the bonding or coupling of smaller molecules to form a larger molecule. One skilled in the art would  
5 recognize that the term "polymerization" is intended to include a range of different degrees of polymerization, *i.e.*, ranging from a single reaction, *e.g.*, two molecules reacting to form a dimer, to a plurality of reactions, *e.g.*, a large number of molecules reacting to form a macromolecule.

The language "scaffolding functionality" refers to functional moieties, such as  
10 organic functionalities, *e.g.*, of organosilanes, that are capable of chemically interacting with a surface of a second material, *e.g.*, a containment vessel, thus allowing the PSN material to anchor to the second material, and thereby become immobilized relative thereto. In certain embodiments of the invention, the functional moiety is a  
"polymerizable group" including, but not limited to vinyl, acrylate, methacrylate, *e.g.*, 3-  
15 methacryloxypropyl, acrylamide, methacrylamide, styrene, *e.g.*, styrylethyl, divinylbenzene, itaconate, fumarate, alkyne, and combinations thereof. The ordinarily skilled artisan would understand that the scaffolding functionality would be consumed during a polymerization reaction to varying extents depending on the reaction conditions chosen, and that the above listed functionalities are provided in their unreacted or  
20 monomeric state.

The language "second material" is intended to include any second material with a surface capable of receiving the PSN material.

The language "surface modifiers" is intended to include functionalizing groups that impart a certain chromatographic functionality to a chromatographic stationary  
25 phase. Surface modifiers such as disclosed herein are attached to the base material, *e.g.*, *via* derivatization or coating and later crosslinking, imparting the chemical character of the surface modifier to the base material.

The language "wall adhesion" refers to a property of a material, *e.g.*, a PSN material, in which the material possesses sufficient chemical interaction between the  
30 material and a second material (*e.g.*, the inside wall of a capillary column) such that the chemical interactions are retained upon subjection of the material to additional factors, *e.g.*, during use of the material in chromatographic separations. In certain embodiments, the PSN material possesses sufficient wall adhesion so as to minimize or preclude flow paths between the PSN material and the second material, *e.g.*, chromatographic column,  
35 where said flow paths would be deleterious to separation efficacy in the chromatographic column.

## I. Compositions of Matter

In one aspect, the invention provides a hybrid inorganic/organic material comprising a polymerized scaffolding nanocomposite (PSN), wherein the  
5 nanocomposite contains a scaffolding functionality capable of chemically interacting with a surface of a second material. The hybrid material includes inorganic-based structures wherein an organic functionality is integral to both the internal or "skeletal" inorganic structure, wherein the inorganic portion is selected from, but not limited to silica, alumina, zirconium oxide, titanium oxide, ceramics, tin oxide, and combinations  
10 thereof.

In certain embodiments, the organic functionality of the hybrid material is derived, at least in part, from a hybrid monomer, *e.g.*, an organosilane, *e.g.*, an organoalkoxysilane, which comprises both an inorganic and organic component, *i.e.*, relating to the presence of both a silicon-oxygen bond and a carbon-silicon bond in a  
15 single monomeric unit. In certain embodiments, the organosilane is an organoalkoxysilane having the formula  $R^2Si(OR^1)_3$  or  $R^6[Si(OR^1)_3]_m$  where  $R^2$  is a styryl, vinyl, an acrylate, methacrylate, acrylamide, methacrylamide, divinylbenzene, itaconate, fumarate, substituted or unsubstituted  $C_1 - C_{18}$  alkenylene, alkynylene or arylene, or a combination thereof;  $R^1$  is a  $C_1 - C_4$  alkyl moiety;  $R^6$  is a substituted or  
20 unsubstituted  $C_1 - C_{18}$  alkenylene, alkynylene or arylene moiety bridging two or more silicon atoms; and  $m$  is an integer greater than or equal to two. In certain embodiments,  $R^2$  is vinyl, methacryloxypropyl, methacrylamidepropyl, or styrylethyl and  $R^1$  is methyl or ethyl; or  $R^6$  is a bridging *N,N*-bis(propylene) acrylamide group,  $m = 2$ , and  $R^1$  is ethyl or methyl. In a specific embodiment of the invention, the organosilane is (3-  
25 methacryloxypropyl)trimethoxysilane. In certain embodiments, the organosilane is minimally water soluble, *e.g.*, sufficient to produce a polymerized scaffolding nanocomposite.

In one embodiment, the PSN is the product of a reaction of a hybrid organic/inorganic monomer, *e.g.*, an organosilane, and an inorganic monomer, *e.g.*, a  
30 silane monomer. In a specific embodiment, the PSN is the product of a reaction of a tetraalkoxysilane and an organosilane containing at least one polymerizable group, *e.g.*, 3-methacryloxypropyl or styrylethyl.

In one embodiment, the tetraalkoxysilane has the formula  $Si(OR^1)_4$ , where  $R^1$  is a  $C_1 - C_3$  alkyl moiety, *e.g.*, tetramethoxysilane or tetraethoxysilane. In certain  
35 embodiments, the organosilane and/or tetraalkoxysilane are minimally water soluble, *e.g.*, sufficient to produce a polymerized scaffolding nanocomposite. In a particular

embodiment, the (3-methacryloxypropyl)trimethoxysilane and the tetramethoxysilane are present in a volume to volume ratio of 1 to 4.

The hybrid inorganic/organic material may be cast in any shape by techniques well known in the art, such as molding, so long as the properties of the material are not substantially affected. In one embodiment of the invention the hybrid inorganic/organic material is a porous hybrid inorganic/organic monolith, *e.g.*, a capillary monolith. The monoliths of the present invention have improved properties including, but not limited to enhanced wall adhesion, *i.e.*, capillary wall adhesion, and increased resistance to shrinkage and improved mechanical stability in comparison to capillary monoliths known in the art.

In certain embodiments of the invention, the polymerizable organo groups are embedded inside the silica skeleton, which yields monoliths that have high surface silanol concentrations, *i.e.*, a large population of chromatographically accessible silanols, and with essentially no chromatographically accessible or useful organo groups. The monolith skeletons of these monoliths are composed of an organic-inorganic nanocomposite, wherein the organic moiety is embedded inside the inorganic silica network. This approach offers monoliths with an increased resistance to shrinkage as well as good resistance to shrinking and swelling upon exposure to organic solvent. In certain embodiments, the shrinkage of the silica skeleton/scaffold will be minimized due to the high organic content. Thus, monolith columns with IDs of greater than 50  $\mu\text{m}$ , *e.g.*, 1-2 mm, can be prepared *in-situ* using this method of reaction.

In an alternate embodiment, the polymerized organic phase is chromatographically accessible and changes the hydrophobicity of the porous surface, resulting in novel selectivities for chromatographic separations. In certain embodiments, the extent to which the organic phase is chromatographically accessible depends on the extent to which the scaffolding functionality is consumed upon anchoring of the PSN material to the interior surface of the chromatographic column. In particular embodiments, unpolymerized scaffolding functionality may directly, *e.g.*, methacrylate groups, or indirectly, *e.g.*, hydrolyzed methacrylate groups, provide the chromatographically accessible organic phase. This polymerization reaction may be regulated to produce desired chromatographic selectivities.

In accordance with the invention, the PSN contains a scaffolding functionality that is capable of chemically interacting with a surface of a second material, *e.g.*, a containment vessel, thus allowing the PSN material to anchor to the second material. In certain embodiments of the invention, the scaffolding functionality is a "polymerizable group" including, but not limited to vinyl, acrylate, methacrylate, *e.g.*, 3-

methacryloxypropyl, acrylamide, methacrylamide, styrene, *e.g.*, styrylethyl, divinylbenzene, itaconate, fumarate, alkyne, and combinations thereof.

5 The improved properties afforded by the invention, *e.g.*, enhanced wall adhesion and/or increased resistance to shrinkage, are the result of the scaffolding functionality that anchors the polymer to the wall of the containment vessel. The ordinarily skilled artisan would understand that the scaffolding functionality would be substantially consumed during a polymerization reaction, and that the above-listed functionalities are provided in their unreacted or monomeric state.

10 The second material, in accordance with the invention, is any material having a surface that is capable of receiving the PSN material. In certain embodiments, the second material is a containment vessel, which provides supportive enclosure to the PSN material. The second material, *e.g.*, containment vessel, may be used as the primary reaction vessel for preparation of the PSN material, or the PSN material may be prepared independently of the second material and subsequently transferred to the second  
15 material, *e.g.*, a secondary containment vessel, such that the PSN material is capable of interacting with the second material.

In one embodiment, the containment vessel is used as the reaction vessel, whereby chemical interactions, such as chemical bonding, *e.g.*, covalent bonding, occur between the forming PSN material and the second material during the polymerization of  
20 the PSN material. In an alternative embodiment, the PSN material is subsequently transferred to the second material, such as a secondary containment vessel, wherein chemical interactions, such as chemical bonding, *e.g.*, covalent bonding, occur through further chemical processing, *e.g.*, addition of a crosslinking agent, photoinitiation of a radical polymerization reaction, or addition of a hydrosilylation catalyst for a  
25 hydrosilylation reaction. The containment vessels that may be utilized for PSN materials of the present invention include, but are not limited to a chromatographic column, *e.g.*, capillary column, *e.g.*, a fused silica capillary column, a glass lined steel column, a radial compression column, a trap column, a microfluidic device, a microchip, a sensor, an electronic circuit, a solid phase extraction (SPE) device, *e.g.*, a miniaturized SPE device,  
30 and an on-column frit.

In certain embodiments, the second material in itself has functionality suitable for interaction with the nanocomposite. In other embodiments, the surface of the second material is derivatized with an anchoring functionality or treated to provide the anchoring functionality.

35 The anchoring functionality and the scaffolding functionality may be copolymerizable, such that a covalent bond is formed as a result of copolymerization of

the scaffolding and anchoring functionalities. In one embodiment, this polymerization may be initiated by a radical initiator, including, but not limited to 2,2'-azobis(isobutyronitrile), 2,2'-azobis(2-methylpropionamidine) dihydrochloride, 4,4'-azobis(4-cyanovaleric acid), potassium persulfate, and peracetic acid. In addition, the  
5 radical initiator is at least minimally soluble, *e.g.*, minimally water soluble.

In certain embodiments, the present invention involves the interaction of silanol functionalities, *e.g.*, chemical bonding between a silanol of second surface and a silanol of the PSN material (*i.e.*, a glass capillary surface containing silanols that react with the Si-OH groups of a silica sol to form a bridging siloxane between a gelling monolith and  
10 the capillary wall). However, it should be understood that in certain embodiments where the chemical interaction is the interaction of silanol functionalities, this interaction is in combination with other chemical interaction(s), *e.g.*, chemical bonding, through polymerization, *e.g.*, forming an organic chemical bond. In certain other embodiments the chemical interaction is not the interaction of silanol functionalities.

15 In another aspect, the invention provides a PSN that is a composite material prepared by the polymerization sol-gel reaction described herein below. For example, in one embodiment, the preparation of a PSN material comprises the steps of

- a) forming a sol-gel by the reaction of two or more monomers;
- b) initiating a polymerization reaction; and
- 20 c) allowing the monomers to react through a polymerization sol-gel (PSG) reaction.

In certain embodiments, the preparation of the PSN may further comprise the step of (d) modifying the pore structure of the material. The porous inorganic/organic hybrid materials of the invention may be used as prepared by the process noted above  
25 and further described in Section II below, without further modification.

Alternatively, the hybrid materials of the invention may be further modified by one or more processing treatments, *e.g.*, by: chemical processing treatment, such as derivatization of surface functionalities of the thus-prepared material; incorporating additives to the PSG reaction that affect the physical properties, *e.g.*, porogens, such as  
30 surfactants or solvents, *e.g.*, toluene; physical processing treatments, such as hydrothermal treatment; or a combination of several processing treatments.

### Chemical Processing

#### *A. Incorporation of Additives*

In one embodiment, the pore structure of the materials of the invention, *e.g.*, monolith materials, is modified by further including a surfactant or combination of different surfactants in the PSG reaction. In a specific embodiment, the surfactant or combination of surfactants includes at least one nonionic surfactant. Exemplary  
5 nonionic surfactants include but are not limited to surfactants comprised of block copolymers of polyethylene glycol and polypropyleneglycol, surfactants comprised of alkylphenoxypolyethoxyethanol, and polyethyleneglycol, *e.g.*, Pluronic F38. In particular embodiments, the surfactant or combination of surfactants are selected from surfactants with a hydrophile-lipophile balance ranging from about 0 to 60, *e.g.*, about  
10 10 to 50, *e.g.*, about 20 to 40, *e.g.*, about 30 to 40, *e.g.*, about 33.

The surfactants are believed to enhance the concentration of water and the acid/base catalyst on the surface of the material during the polymerization sol-gel reaction. Use of surfactants to modulate the surface structure of the material stabilizes the polymer material that is forming throughout the reaction, and minimizes or  
15 suppresses inhomogeneous morphology.

#### *B. Surface Modification*

The methods of preparation may further comprise surface modifying the materials of the invention, *e.g.*, the monolith materials of the invention. The hybrid  
20 materials of the invention possess both organic groups and silanol groups, which may be additionally substituted or derivatized with a surface modifier.

In one embodiment of the invention, surface organic groups of the porous inorganic/organic hybrid material are derivatized or modified in a subsequent step *via* formation of an organic covalent bond between the modifying reagent and organic  
25 groups of the material, wherein the material retains sufficient scaffolding functionality such that the material is able to interact with a second material. Alternatively, the surface silanol groups of the hybrid silica are derivatized into siloxane organic groups, such as by reacting with an organotrihalosilane, *e.g.*, octadecyltrichlorosilane, or a halopolyorganosilane, *e.g.*, octadecyldimethylchlorosilane. Alternatively, the surface  
30 organic and silanol groups of the hybrid silica are both derivatized.

In a particular embodiment, the silanol groups are surface modified with compounds having the formula  $Z_a(R')_b\text{Si-R}$ , where  $Z = \text{Cl, Br, I, C}_1 - \text{C}_5 \text{ alkoxy, dialkylamino or trifluoromethanesulfonate}$ ;  $a$  and  $b$  are each an integer from 0 to 3 provided that  $a + b = 3$ ;  $R'$  is a  $\text{C}_1 - \text{C}_6$  straight, cyclic or branched alkyl group, and  $R$  is  
35 a functionalizing group.  $R'$  may be, *e.g.*, methyl, ethyl, propyl, isopropyl, butyl, t-butyl,

sec-butyl, pentyl, isopentyl, hexyl or cyclohexyl; preferably, R' is methyl. In additional embodiments, the organic groups may be similarly functionalized.

In one embodiment, the organic groups of the hybrid materials react to form an organic covalent bond with a surface modifier. The modifiers can also form an organic  
5 covalent bond to the material's organic group *via* a number of mechanisms well known in organic and polymer chemistry including but not limited to nucleophilic, electrophilic, cycloaddition, free-radical, carbene, nitrene, and carbocation reactions.

In one embodiment, the surface modifier may be an organotrihalosilane, such as octyltrichlorosilane or octadecyltrichlorosilane. In an additional embodiment, the  
10 surface modifier may be a halopolyorganosilane, such as octyldimethylchlorosilane or octadecyldimethylchlorosilane. In certain other embodiments the surface modifier is octadecyldimethyl-N,N-dimethylaminosilane.

In another embodiment, the surface of the hybrid silica material may also be surface modified by coating with a polymer. Polymer coatings are known in the  
15 literature and may be provided generally by polymerization or polycondensation of physisorbed monomers onto the surface without chemical bonding of the polymer layer to the support (type I), polymerization or polycondensation of physisorbed monomers onto the surface with chemical bonding of the polymer layer to the support (type II), immobilization of physisorbed prepolymers to the support (type III), and chemisorption  
20 of presynthesized polymers onto the surface of the support (type IV)<sup>(11)</sup>. As noted above, coating the hybrid material with a polymer may be used in conjunction with various surface modifications described in the invention.

Moreover, the surface of the materials of the invention may contain residual organic groups, which can be derivatized by reacting with a reagent that is reactive  
25 towards the organic group. For example, vinyl groups, *e.g.*, unreacted methacrylate groups, on the particle can be reacted with a variety of olefin reactive reagents such as bromine (Br<sub>2</sub>), hydrogen (H<sub>2</sub>), free radicals, propagating polymer radical centers, dienes, and the like. In another example, hydroxyl groups on the material can be reacted with a variety of alcohol reactive reagents such as isocyanates, carboxylic acids, carboxylic acid  
30 chlorides, and reactive organosilanes as described below. Reactions of this type are well known in the literature, *see, e.g.*, March, J. "Advanced Organic Chemistry," 3<sup>rd</sup> Edition, Wiley, New York, 1985; Odian, G. "The Principles of Polymerization," 2<sup>nd</sup> Edition, Wiley, New York, 1981; the texts of which are incorporated herein by reference. Moreover, regulation of the extent of the (methacrylate) polymerization reaction may be  
35 used to supply more or less organic groups for derivatization with reagents that are reactive to the organic functionalities.

In addition, the surface of the materials of the invention contain silanol groups, which can be derivatized by reacting with a reactive organosilane. The surface derivatization of the hybrid material may be conducted according to standard methods, for example by reaction with octadecyltrichlorosilane or octadecyldimethylchlorosilane in an organic solvent at elevated temperature. An organic solvent such as toluene or methylene chloride is typically used for this reaction. An organic base such as pyridine or imidazole is added to the reaction mixture to catalyze the reaction. The product of this reaction is then washed with one or more solvents such as methanol, water, toluene, methylene chloride, and/or acetone and can be sometimes further dried at about 80°C to 100°C under reduced pressure for about 16 h. The resultant hybrid material can be further reacted with a short-chain silane such as trimethylchlorosilane to endcap any remaining silanol groups, by using a similar procedure described above.

### C. *Hydrothermal Treatment*

In addition, materials of the invention, *e.g.*, the monolith materials of the invention, may be subjected to hydrothermal treatment to improve the material's pore structure, *e.g.*, by further condensation of the siloxane polymer network formed during the PSG reaction, and dissolution and redeposition of silicic acid silicates from and to the surface of the pore structure. In particular, this treatment would be applicable after the polymerization achieved a solid state. In one embodiment, the hydrothermal treatment is in a basic solution at an elevated or high temperature, *e.g.*, 120 °C (*i.e.*, the hydrothermal treatment is run in the capillary). The range of pH of the hydrothermal treatment is about 6-12, *e.g.*, about 8-11, *e.g.*, about 9-10. The monolith material is then rinsed with water followed by a solvent exchange, *e.g.*, with methanol; ethanol; acetonitrile; or tetrahydrofuran followed by room temperature, *e.g.* about 20-25 °C, drying. The material is then dried at about 25-120 °C, and preferably at about 70 °C, under vacuum overnight.

In one embodiment, the condensation is base catalyzed, *e.g.*, by ammonia. In certain embodiments, the ammonia is generated by the high temperature decomposition of urea or a suitable organic amide.

The surface of the hydrothermally treated hybrid material may be modified in a similar fashion to that of the hybrid material that is not modified by hydrothermal treatment as described above. For example, in a subsequent step, the surface organic groups of the hybrid material may be optionally modified *via* formation of a covalent bond between the monolith material's organic and/or silanol group and the modifying reagent, and optionally including coating with a polymer, *i.e.*, also as is described above.



## II. Methods of Preparation

In a related aspect, the invention provides a method of preparation of a hybrid inorganic/organic material comprising a polymerized scaffolding nanocomposite (PSN),  
5 comprising the steps of

- a) forming a sol-gel by the reaction of two or more monomers;
- b) initiating a polymerization reaction; and
- c) allowing the monomers to react through a polymerization sol-gel (PSG)  
10 reaction, thereby preparing the hybrid inorganic/organic monolith, wherein the monolith contains a scaffolding functionality capable of chemically interacting with a surface of a second material. In certain embodiments, the methods further comprise the step of (d) modifying the pore structure of the material. As described above, the resulting PSN material may be subsequently transferred to the second material, such as a secondary containment vessel, wherein chemical interactions, such as chemical bonding, *e.g.*,  
15 covalent bonding, occur through further chemical processing, *e.g.*, addition of a crosslinking agent, photoinitiation of a radical polymerization reaction, or addition of a hydrosilylation catalyst for a hydrosilylation reaction.

Alternatively, the invention provides a method for *in situ* preparation of a hybrid inorganic/organic monolith in a chromatographic column, *e.g.*, a capillary column, *e.g.*, a  
20 fused-silica capillary column. The method comprises:

forming an anchoring functionality on an interior surface of said chromatographic column; and

forming inside the chromatographic column a hybrid inorganic/organic monolith comprising a polymerized scaffolding nanocomposite (PSN), wherein the  
25 nanocomposite contains a scaffolding functionality capable of chemically interacting with the anchoring functionality on the surface, the monolith being formed by:

- a) forming a sol-gel by the reaction of two or more monomers;
- b) initiating a polymerization reaction; and
- c) allowing the monomers to react through a polymerization sol-gel (PSG)  
30 reaction; whereby the scaffolding functionality and the anchoring functionality chemically interact to thereby anchor the monolith to the surface, such that a hybrid inorganic/organic monolith is prepared *in situ* in the chromatographic column. In certain embodiments, the *in situ* process involves covalent bond formation between the PSN

material and the surface of the chromatographic column, *i.e.*, consumption of a plurality of scaffolding functionalities in covalent bond formation to the second material.

In accordance with these aspects of the invention, the hybrid materials are prepared using a polymerization sol-gel (PSG) reaction. More particularly, the hybrid materials are prepared using simultaneous polymerization reactions and sol-gel reactions, wherein the organic and inorganic nanophases interconnect by chemical bond formation through an interaction with a hybrid monomer, *e.g.*, by condensation of the inorganic phase, *e.g.*, of the hybrid monomer to an inorganic monomer; and polymerization of the organic phase, *e.g.*, radical polymerization, such that a hybrid material forms. In a particular embodiment, the materials are made from a mixture of a tetraalkoxysilane, *e.g.*, tetramethoxysilane, and a polymerizable organosilane, *e.g.*, (3-methacryloxypropyl)trimethoxysilane, wherein the organosilane is minimally water soluble, *e.g.*, sufficient to produce a polymerized scaffolding nanocomposite (*i.e.*, the polymerizable group will have an affect on this solubility).

In one exemplary embodiment, the PSG reaction begins with hydrolysis, *e.g.*, acid catalyzed hydrolysis, *e.g.*, by acetic acid, and slow condensation of a hybrid monomer and an inorganic monomer, *e.g.*, a mixture of tetramethoxysilane and a polymerizable organosilane, such as (3-methacryloxypropyl)trimethoxysilane, and proceeds at low temperature (*e.g.*, a temperature ranging from about 0 °C to about room temperature, *e.g.* about 20-25 °C) and low pH (*e.g.*, about 2-3), forming a mixture of low molecular weight oligomers. In a subsequent step, a polymerization reaction is initiated, *e.g.*, radically initiated. In certain embodiments, the radical initiation occurs at an increased temperature (*e.g.*, above room temperature, *e.g.*, about 60-65 °C). The oligomers formed are then simultaneously polymerized, *e.g.*, *via* radical chain polymerization, and further condensed to form a polymerized sol-gel (illustrated in Figure 1). Moreover, the polymerizable group (depicted in Figure 1A, in both chemical structure and schematic form) may react with additional polymerizable groups or terminate in a reaction with the surface of a second material, *e.g.*, with an anchoring functionality on the inner surface of a chromatographic column. A simplified example of the product of the polymerization sol-gel reaction is shown in a cross-sectional block of an interior portion of the PSN material in Figures 1C and 1D, *i.e.*, polymerization to the second material is not depicted. However, the depictions of Figure 1 are not intended to limit the scope of the invention.

The PSG reaction is performed at a temperature sufficient to achieve simultaneous polymerization and sol gel reactions, *e.g.*, at 65 °C, and is performed for an amount of time sufficient to prepare the hybrid inorganic/organic material, *e.g.*, the PSN material. In certain embodiments, the polymerization is initiated with a radical initiator,

*e.g.*, a radical initiator that is minimally water soluble, *e.g.*, 2,2'-azobis(isobutyronitrile), 2,2'-azobis(2-methylpropionamidine) dihydrochloride, 4,4'-azobis(4-cyanovaleric acid), potassium persulfate, or peracetic acid. In certain embodiments of the invention, the sol-gel reaction occurs in the presence of urea.

5

### III. Devices

The porous inorganic/organic hybrid materials of the current invention have a wide variety of end uses in the separation sciences, such as materials for chromatographic columns, thin layer chromatographic (TLC) plates, filtration  
10 membranes, microtiter plates, scavenger supports, solid phase organic synthesis supports, Capillary-LC columns, radial compression columns, trap columns, microfluidic devices, microchips, sensors, electronic circuits, miniaturized solid phase extraction (SPE) devices and on-column frits, and the like, having a stationary phase that includes porous inorganic/organic hybrid materials, *e.g.*, monolith materials, of the  
15 present invention. The stationary phase may be introduced into the device by coating, impregnation, cladding, wrapping, or other art-recognized techniques consistent with the methods of preparation of the present invention, *etc.*, depending on the requirements of the particular device.

Thus, in another aspect, the invention provides a separations device comprising

20

a) a surface capable of accepting a monolith material comprising a polymerized scaffolding nanocomposite (PSN) material, said surface comprising an anchoring functionality and

b) a hybrid inorganic/organic monolith comprising a polymerized scaffolding nanocomposite (PSN), wherein the nanocomposite contains a scaffolding  
25 functionality capable of chemically interacting with the anchoring functionality on said surface, and wherein said hybrid organic/inorganic monolith is anchored to said surface by a chemical interaction between said scaffolding functionality and anchoring functionality. In certain embodiments, the devices in accordance with the invention include chromatographic columns, *e.g.*, a glass lined steel column, capillary column, thin  
30 layer plates, filtration membranes, sample cleanup devices, and microtiter plates.

In certain embodiments, the separations device is a fused-inorganic capillary column, wherein the inorganic portion may be selected from, but is not limited, to silica, alumina, zirconium oxide, titanium oxide, ceramics, tin oxide, and combinations thereof.

In an particularly advantageous embodiment, the invention provides a chromatographic column, *e.g.*, a capillary column, *e.g.*, a fused-silica capillary column, comprising

- 5 a) a chromatographic column having a cylindrical interior surface capable of accepting a monolith comprising a polymerized scaffolding nanocomposite (PSN) material, the interior surface comprising an anchoring functionality, and
- b) a hybrid inorganic/organic monolith comprising a polymerized scaffolding nanocomposite (PSN), wherein the nanocomposite contains a scaffolding functionality capable of chemically interacting with the anchoring functionality on the surface, and wherein the hybrid organic/inorganic monolith is anchored to the surface by a chemical interaction between the scaffolding functionality and anchoring functionality.
- 10

In certain embodiments, the device is a chromatographic column, *e.g.*, a capillary column, *e.g.*, a fused-silica capillary column, wherein the interior surface of the capillary column is derivatized with a polymerizable anchoring functionality. In certain

15 embodiments of the invention the capillary column has an inner diameter (I.D.) greater than about 50  $\mu\text{m}$ , *e.g.*, greater than about 100  $\mu\text{m}$ , *e.g.*, greater than about 150  $\mu\text{m}$ , *e.g.*, greater than about 200  $\mu\text{m}$ , *e.g.*, greater than about 250  $\mu\text{m}$ , *e.g.*, greater than about 500  $\mu\text{m}$ , *e.g.*, greater than about 1.0 mm, *e.g.*, greater than about 2 mm, *e.g.*, greater than about 3 mm. In a particularly advantageous embodiment, the chromatographic device is

20 a chromatographic column, such as commonly used in HPLC.

### Examples

The present invention may be further illustrated by the following non-limiting examples describing the preparation of porous inorganic/organic hybrid monolith

25 materials, and their use.

### *Materials*

All reagents were used as received unless otherwise noted. Those skilled in the art will recognize that equivalents of the following supplies and suppliers exist, and as

30 such the suppliers listed below are not to be construed as limiting.

Gelest Inc., Morrisville, PA: (3-Methacryloxypropyl)trimethoxysilane (MAPTMOS), tetramethoxysilane (TMOS), and octadecyldimethyl(dimethylamino)silane; BASF Corp., Mount Olive, NJ: Pluronic® F38; Sigma-Aldrich Chemical Co., Milwaukee, WI: thiourea, acenaphthene, naphthalene, sodium hydroxide; DuPont, Wilmington, DE, Vazo® 64 and Vazo® 44; J.T. Baker, Phillipsburgh, NJ: urea, methylene chloride, methanol, acetonitrile, acetone, toluene, pyridine, hydrochloride acid and glacial acetic

35

acid. All solvents were HPLC grade. Water was used directly from a Millipore Milli-Q (Millipore Corp., Bedford, MA). Fused silica capillary columns (Cat # FS-115, 150  $\mu$ m I.D., Cat # FS-150, 50  $\mu$ m I.D., or equivalents) and all the end-fittings and unions (Cat #P-760) were from Upchurch Scientific (Oak Harbor, WA) and from Polymicro Technologies, Phoenix, AZ (Cat # TSP 530660, 520  $\mu$ m I.D., or equivalents). Compression screws were from Waters Corp. (Milford, MA.).

### EXAMPLE 1

10

A Harvard Apparatus Model '33' Dual Syringe Pump (Harvard Apparatus Inc., Holliston, MA, or equivalent) and 10 mL Pharmaseal<sup>®</sup> syringe (American Pharmaseals Laboratory, Glendale, CA, or equivalent) were used in all capillary filling and purging steps.

15

A fused silica capillary column (*ca.* 2 m in length) was treated by the following five steps: (1) the column was purged with 1N NaOH at a flow rate of 50  $\mu$ L/min for at least 5 minutes, sealed via compression fittings and heated to 90 °C for 17 hours; (2) the column was purged with 1N HCl water solution at a flow rate of 50  $\mu$ L/min for at least 5 minutes; (3) the column was rinsed with water, acetone, and then toluene at a flow rate of 50  $\mu$ L/min for 10 minutes each (total volume ~500  $\mu$ L, >10 times column volume); (4) the column was filled with a mixture of 0.5 mL (3-methacryloxypropyl)trimethoxysilane / 0.5 mL pyridine/10 mL toluene at a flow rate of 50  $\mu$ L/min for 5 minutes, sealed at both ends of the column and the column was then heated in a 90 °C oven for 21 hours; and (5) the column was washed with toluene, acetone and water for 10 minutes each at a flow of 50  $\mu$ L/min.

20  
25

After surface derivatization, sections of the 2 meter capillary are cut to make multiple, shorter capillary monoliths that may be used in further experiments.

30

### EXAMPLE 2

Pluronic<sup>®</sup> F38 (Example 2a - 0.622 g, Example 2b - 0.596 g) and urea (Example 2a - 0.517 g, Example 2b - 0.515 g) were added to 5 mL of a 15 mM acetic acid solution at room temperature in a glass vial. The solutions were deoxygenated by nitrogen gas purging for at least 2 minutes before Vazo<sup>®</sup> 64 (1-2 mg) was added, and then the solution was cooled to 0 °C. In a separate glass vial, a 2 mL silane mixture (4/1

35

TMOS:MAPTMOS v/v) was prepared and then cooled to 0 °C. Next, the silane mixture was added slowly to the acetic acid solution. The combined solutions were stirred at 0 °C for 1 h and then at room temperature (rt) for 1.75 h.

5 The resulting solutions were delivered into two separate 50 µm (I.D.) x 40 mm (L) capillary columns that were surface treated as described in Example 1 with the exception that step (1) was run for 2 hours. The columns were then sealed at both ends with two compression screws and were heated at 45 °C in an oven for 18.5 h.

10 Monolith morphology of the cross-sections of each column was observed by Scanning Electron Microscopy (SEM) (JEOL, Peabody, MA or equivalent) and showed the formation of monolith materials with a majority of macropores with diameters greater than 0.5 µm and the absence of shrinkage away from the capillary wall.

### EXAMPLE 3

15

As described in Example 2, Pluronic® F38 and urea were added to 5 mL of an acetic acid solution at room temperature. The solutions were deoxygenated by nitrogen gas purging for at least 2 minutes before Vazo® 64 was added. The stirred solutions were cooled to 0 °C for a specific time, and 2 mL of a 0 °C silane mixture (4/1  
20 TMOS:MAPTMOS v/v) was added slowly to the acetic acid solution. The combined solutions were stirred at 0 °C for a prescribed time and then at rt for an additional time period.

25 The resulting solutions were delivered into separate 150 µm (I.D.) x 40 mm (L) capillary columns that had been surface treated as described in Example 1. The columns were then sealed at both ends with two compression screws and were heated at 65 °C for a prescribed time and then at an elevated temperature (Example 3a,b 120°C; Example 3c-j 105°C; Example 3k-o 110°C; Example 3p-t 125°C) for an additional time period.

30 Monolith morphology of the cross-sections of each column was observed by SEM as described in Example 2. Depending on the reaction conditions, dense monolith materials (a majority of macropores with diameters less than 0.5 µm) to non-dense monolith materials (a majority of macropores with diameters greater than 0.5 µm) were observed, and varying levels of wall adhesion were achieved. Specific amounts of reagents used to prepare these products and characterization data are listed in Table 1.

35 Example 3k and 3t were cut to 20 cm lengths and the surfactant was removed from the monolith structure by prolonged methanol purging using an Eldex Micropro

Syringe Pump (Eldex, Napa, CA, or equivalent). The column was purged with methanol for 5 days at a 1.0  $\mu\text{L}/\text{min}$  flow rate, at which time no surfactant could be detected in the mobile phase as measured by FTIR spectroscopy (Polaris, ThermoMattson, Madison, WI, or equivalent).

5

*Surface Modification:*

After chromatographic evaluation as described in Example 9 (see Table 4), Example 3t was purged with methylene chloride at 1.0  $\mu\text{L}/\text{min}$  for 16h and then purged with a solution of octadecyldimethyl(dimethylamino)silane in methylene chloride (1/4 v/v) at 1  $\mu\text{L}/\text{min}$  for 3 h. After surface modification, the column was purged with methylene chloride at 1  $\mu\text{L}/\text{min}$  flow rate for 16 hours, which was then exchanged with acetonitrile by purging with greater than 3 column volumes. The resulting surface modified monolith is identified as Example 3u, which was in turn evaluated as described in Example 9 (see Table 4).

15

#### EXAMPLE 4

As described in Example 2, Pluronic® F38 and urea were added to 5 mL of an acetic acid solution at room temperature. The solutions were deoxygenated with  $\text{N}_2$  purge for at least 2 minutes before Vazo® 64 was added. The stirred solutions were cooled to 0 °C for a specific time, and 2 mL of a 0 °C silane mixture (4/1 TMOS:MAPTMOs v/v) was added slowly to the acetic acid solution. The combined solutions were stirred at rt for prescribed time.

The resulting solutions were delivered into separate 150  $\mu\text{m}$  (I.D.) x 40 mm (L) capillary columns that were surface treated as described in Example 1. The columns were then sealed at both ends with two compression screws and were heated at 65 °C for a prescribed time and then at an elevated temperature (4a-e 120°C; 4f-n 110°C) for an additional time period.

Monolith morphology on the cross-section of the column was observed by SEM as described in Example 2. Depending on the reaction conditions, dense monolith materials (a majority of macropores with diameters less than 0.5  $\mu\text{m}$ ) to non-dense monolith materials (a majority of macropores with diameters greater than 0.5  $\mu\text{m}$ ) were observed, and varying levels of wall adhesion were achieved. Specific amounts of reagents used to prepare these products and characterization data are listed in Table 2.

TABLE 1

Product	HOAc (mM)	Pluronic F38 (g)	Urea (g)	Vazo 64 (mg)	Time 0°C (min)	Time rt (h)	Time 65°C (h)	Time elevated temp (h)	Dense (Y/N)	Wall Adhesion (Y/N)
3a	15	0.715	0.508	5	30	60	15	8	Y	N
3b	30	0.708	0.503	5	30	1	18	7	Y	Y
3c	15	0.709	0.502	5	0	3	17	5	Y	Y
3d	30	0.698	0.501	5	0	3	17	5	Y	N
3e	15	0.797	0.509	3	0	3	17	5	Y	N
3f	30	0.793	0.511	3	0	3	17	5	Y	N
3g	15	0.695	0.511	5	0	3	17	5	Y	N
3h	15	0.793	0.504	5	0	3	17	5	Y	N
3i	15	0.593	0.511	4	0	4	5	72	N	Y
3j	15	0.558	0.496	4	0	4	5	72	N	Y
3k	30	0.561	0.502	0.5	0	3	2	18	N	Y
3l	30	0.595	0.498	1	0	3	2	18	Y	N
3m	30	0.659	0.496	1	0	3	2	18	Y	N
3n	30	0.703	0.497	1	0	3	2	18	Y	N
3o	30	0.790	0.496	1	0	3	2	18	Y	N
3p	30	0.560	0.499	1	0	3	2	16	N	Y
3q	30	0.533	0.508	3	0	3	2	16	N	N
3r	30	0.508	0.508	6	0	3	2	16	N	Y
3s	30	0.470	0.513	5	0	3	2	16	N	N
3t	30	0.415	0.501	2	0	3	2	16	N	Y



TABLE 2

Product	HOAc (mM)	Pluronic F38 (g)	Urea (g)	Vazo 64 (mg)	Time rt (h)	Time 65°C (h)	Time elevated temp (h)	Dense (Y/N)	Wall Adhesion (Y/N)
4a	50	0.605	0.484	1	2	4	17	N	Y
4b	50	0.505	0.512	2	2	4	17	N	Y
4c	50	0.401	0.518	2	2	4	17	N	Y
4d	50	0.704	0.500	2	2	4	17	N	N
4e	50	0.358	0.495	3	2	4	17	N	Y
4f	50	0.403	0.502	1	2	20	8	N	Y
4g	70	0.418	0.500	1	2	20	8	N	Y
4h	100	0.400	0.492	1	2	20	8	N	N
4i	50	0.404	0.493	1	4	3	17	N	N
4j	70	0.419	0.492	1	4	3	17	N	N

TABLE 3

Product	HOAc (mM)	Pluronic F38 (g)	Urea (g)	Vazo 44 (mg)	Time rt (h)	Time 60°C (h)	Time 100°C (h)	Dense (Y/N)	Wall Adhesion (Y/N)
8a	50	0.694	0.486	20	2	17	72	Y	N
8b	50	0.653	0.501	20	2	17	72	N	Y
8c	50	0.649	0.546	2	1	2	17	Y	N
8d	50	0.659	0.514	2	1	2	17	N	Y
8e	50	0.640	0.530	2	1	2	17	Y	N
8f	50	0.628	0.556	2	1	2	17	Y	N
8g	50	0.674	0.553	2	1	2	17	N	Y

### EXAMPLE 5

Pluronic® F38 (0.424 g) and 0.503 g urea were added to 5 mL of a 15 mM acetic acid solution at room temperature in a glass vial. The solutions were deoxygenated by nitrogen gas purging for at least 2 minutes before 3 mg of Vazo® 64 was added, and then the solution was cooled to 0 °C. In a separate glass vial, a 2 mL silane mixture (4/1 TMOS:MAPTMOS v/v) was prepared and then cooled to 0 °C. Next, the silane mixture was added slowly to the acetic acid solution. The combined solutions were stirred at 0 °C for 1 h and then at room temperature (rt) for 1.75 h.

The resulting solution was delivered into a fused silica capillary with a length of 40 cm (Examples 5a-b) or 120 cm (Examples 5c-d), and an inner diameter of 150 µm (Examples 5a-c) or 520 µm (Example 5d), which was pretreated as described in Example 1, at a flow rate of 50 µL/min for 5-7 minutes.

The column was then sealed at both ends using compression screws (Examples 5a-b) or Upchurch P760 compression fittings and a single Upchurch P760 union (Examples 5c-d). The sealed column was held at room temperature for two hours after the mixed silanes were added to the acetic acid mixture. The column was then heated in a 65 °C oven for 2 hours, and transferred to a 125 °C oven and held overnight (20 hours).

The column was then slowly cooled to room temperature. The surfactant was removed from the structure by prolonged methanol purging using an Eldex Micropro Syringe Pump (Eldex, Napa, CA). The column was purged with methanol for 6 hours at a 0.5 µL/min flow rate, then for 20 hours at 1 µL/min flow rate.

Monolith morphology on the cross-section of the column was observed by SEM as described in Example 2. Non-dense monolith materials (a majority of macropores with diameters greater than 0.5 µm) were observed, and wall adhesion was achieved.

### EXAMPLE 6

30

The monolith surfaces of columns from Examples 5a-d were surface modified using the following procedure producing surface modified monoliths defined analogously as Examples 6a-d.

5 A 0.32 M solution of octadecyldimethyl(dimethylamino)silane was prepared in toluene or tetrahydrofuran. The column was purged with this solution using an Eldex Micropro Syringe Pump at a flow rate of 1  $\mu$ L/min for several column volumes and then heated from 25 °C to 50-55 °C and maintained at 50-55 °C for 19 hours. The column was heated using a Hot Pocket column heater (Thermo Hypersil-Keystone, Bellefonte, PA, or equivalent). Upon cooling, methanol was purged through the column at 1  $\mu$ L/min flow rate for at least 5 hours at 35 °C.

10

**EXAMPLE 7**

15 A 1.0 mm I.D. x 150 mm L borosilicate glass lined steel column (SGE Inc., Austin, TX, or equivalent) was surface treated as described in Example 1, with the exception that 6 mL aliquots of solvent was used in step (5). Pluronic® F38 (1.272 g) and urea (1.506 g) were weighed into a glass vial and dissolved into 15.0 mL of a 32 mM acetic acid solution. The mixture was deoxygenated by nitrogen gas purging for 5 minutes before 9 mg of Vazo® 64 were added. The mixture was stirred for 5 minutes at room temperature, and then chilled to 0°C for 23 min.

20 Next, 6 mL of silane mixture (4/1 TMOS:MAPTMOS v/v) was slowly added into the above mixture at 0°C. After silane addition, the mixture was stirred at 0°C for 1.5 h. The resulting mixture was delivered into the glass lined steel column. The column was then sealed at both ends using two Waters stainless steel compression plugs. The sealed column was held at room temperature for two hours after the mixed silanes were added to the acetic acid mixture. The column was heated in a 65 °C oven for 2 hours, and then transferred to a 125 °C oven and held for 18 hours. The column was then slowly cooled to room temperature.

25 The surfactant was removed from the monolith structure by prolonged methanol purging using a HPLC pump (Model 515, Waters Corp, or equivalent). After methanol purging the column end-fittings and frits were removed. Inspection of the monolith structure yielded no evidence of monolith shrinkage, as observed by optical microscope (Model C-P-S, Nikon, Tokyo, Japan, or equivalent).

### EXAMPLE 8

5 Solutions of surfactant, urea, and silane in acetic acid were made as described in Example 4, except Vazo® 44 was substituted for Vazo® 64. The resulting solutions were delivered into separate 150 µm I.D. x 40 mm L capillary columns that were surface treated as described in Example 1. The columns were sealed, heated, and analyzed as described in Example 4, where the elevated temperature was 110 °C. The specific amounts of reagents used to prepare these products and the resulting characterization data are listed in Table 3.

10

### EXAMPLE 9

15 Pressure data on monolith columns were collected on non-surface modified and surface modified monoliths using the pressure transducer of an Eldex MicroPro Syringe Pump (Eldex, Napa, CA, or equivalent). An equivalent particle diameter (apparent particle size) was obtained based on the Kozeny-Carman equation. An interstitial porosity of 0.4 of the particle packed column that would give the same permeability as the monolith bed was assumed. Solvent viscosities of solvent mixtures were obtained  
20 based on the data of Colin *et. al.* [H. Colin, J. C. Diez-Masa, G. Guiochon, T. Czajkowska, I. Miedziak, J. Chromatogr., 167 (1978) 41-65]. Solvent viscosities of neat solvents were obtained from Handbook of Chemistry and Physics on CD-ROM (version 2002, Editor-in-chief D. R. Lide, Chapman & Hall/CRC).

25 Results of the determination of the equivalent particle size are summarized in Table 4.

TABLE 4

Equivalent Particle Size [ $\mu\text{m}$ ] in Selected Solvents					
Product	Methanol	Methylene Chloride	Acetonitrile	Acetonitrile-water 55:45 (v/v)	Acetonitrile-water 40:60 (v/v)
3t	3	4	-	4	-
3u	-	3	4	3	3
5b	4	-	-	-	-
6b	-	-	-	-	4
5c	21	-	-	-	-
6c	-	-	-	-	17
5d	-	-	-	26	-
6d	-	-	-	-	26

5

## EXAMPLE 10

The following example demonstrates the porosity of the hybrid inorganic/organic materials and further characterizes the materials using chromatographic criteria, *i.e.*, efficiency and tailing factor.

10

*Experimental Conditions:*

The experimental data was acquired using an Eldex MicroPro Syringe Pump (Eldex, Napa, CA, or equivalent), a Valco internal sample injector (Valco Instruments Co. Inc., Houston, TX, or equivalent) and a Waters 2487 Dual  $\lambda$  absorbance detector equipped with a 250 nL capillary flow cell (Waters Corp., or equivalent). Data acquisition and determination of chromatography parameters was performed using Millenium 32 software (Waters Corp., or equivalent). Acetonitrile and water was mixed in 40/60 volume ratio. Thiourea, naphthalene and acenaphthene were used as analytes. The pump was operated at volumetric flow rates between 0.25 and 4.0  $\mu\text{L}/\text{min}$ . Thiourea, naphthalene and acenaphthene were dissolved in acetonitrile-water 55:45 (v/v) mixture at 20, 100 and 400  $\mu\text{g}/\text{ml}$  respectively. The injection volume was 20 nL. UV detection was carried out at 254 nm. The experiments were performed at ambient temperature (24  $^{\circ}\text{C}$ ).

25

*Experimental Protocol:*

The columns were directly connected to the injector and to the inlet of capillary flow cell except 3u which was connected with 50  $\mu$ m I.D. fused silica capillaries.

- Results of chromatography evaluation are summarized in Table 5. Total porosity was calculated by dividing the elution volume of non-retained compound (thiourea) by the total column volume.

**TABLE 5**

Column No.	Flow Rate [ $\mu$ L/min]	Test Solute	Capacity Factor	N/ meter (half width)	USP Tailing Factor	Total Porosity
3u	0.25	Naphthalene	3.76	12540	1.27	0.96
	0.5	Naphthalene	3.47	11890	1.40	
	0.75	Naphthalene	3.38	980	1.42	
	0.25	Acenaphthene	7.79	17550	1.21	
	0.5	Acenaphthene	7.24	14450	1.32	
	0.75	Acenaphthene	7.06	12660	1.33	
6b	0.25	Naphthalene	4.55	42123	1.46	0.97
	0.5	Naphthalene	4.69	45205	1.42	
	0.75	Naphthalene	4.61	41095	1.36	
	1.0	Naphthalene	4.62	36986	1.34	
	0.25	Acenaphthene	9.88	49315	1.20	
	0.5	Acenaphthene	10.18	52053	1.29	
	0.75	Acenaphthene	9.88	45204	1.27	
	1.0	Acenaphthene	9.91	39041	1.25	
6c	0.25	Naphthalene	5.2	40650	1.24	0.92
	0.5	Naphthalene	5.2	48260	1.28	
	1.0	Naphthalene	4.9	43700	1.24	
	2.0	Naphthalene	5.0	30270	1.17	
	4.0	Naphthalene	5.2	19207	1.14	
	0.25	Acenaphthene	11.44	56267	1.26	
	0.5	Acenaphthene	11.4	63878	1.28	
	1.0	Acenaphthene	11.0	45397	1.23	
	2.0	Acenaphthene	11.0	29550	1.16	
	4.0	Acenaphthene	11.4	19593	1.14	

### References

- <sup>1</sup>MacNair J.E., etc. *Anal Chem.* 1999, 71, 700
- <sup>2</sup>Svec F., etc. Review *J. Chromatography A*, 2000, 887, 3-29
- <sup>3</sup>Nakanishi K., Tanaka N. etc., *J. High Resol. Chromatogr.* 1998, Vol. 21, No. 8 p477-479; Nakanishi K., Tanaka N. etc., *J Chromatography A* 2002, 960, 85-96
- <sup>4</sup>Nakanishi K., Tanaka N. etc., *J. Chromatography A* 2002, 961, 53-63
- <sup>5</sup>Zare R.N. etc., *Anal. Chem.* 2001, 73, 3921-3926
- <sup>6</sup>Zare R.N. etc. *J. Chromatography A*, 2002, 961, 45-51.
- <sup>7</sup>Zare R.N. etc. US Patent Application 2002/0079257
- <sup>8</sup>Nakanishi K. etc. WO 99/50654
- <sup>9</sup>O. Prucker and J. R  he, *Macromolecules* 1998, 31, 592-601
- <sup>10</sup>O. Prucker and J. R  he, *Macromolecules* 1998, 31, 602-613
- <sup>11</sup>Hanson *et al.*, *J. Chromat. A* 656 (1993) 369-380

### 15 Incorporation By Reference

The entire contents of all patents, published patent applications and other references cited herein are hereby expressly incorporated herein in their entireties by reference.

### 20 Equivalents

Those skilled in the art will recognize, or be able to ascertain using no more than routine experimentation, numerous equivalents to the specific procedures described herein. Such equivalents were considered to be within the scope of this invention and are covered by the following claims. The contents of all references, issued patents, and published patent applications cited throughout this application are hereby incorporated by reference.

*What is claimed is:*

1. A hybrid inorganic/organic material comprising a polymerized scaffolding nanocomposite (PSN), wherein the nanocomposite contains a scaffolding functionality capable of chemically interacting with a surface of a second material.  
5
2. The hybrid material of claim 1, wherein the second material is a containment vessel.
3. The hybrid material of claim 1, wherein the scaffolding functionality is selected from the group consisting of vinyl, acrylate, methacrylate, acrylamide, methacrylamide, styrene, divinylbenzene, itaconate, fumarate, alkyne, and combinations thereof.  
10
4. The hybrid material of claim 1, wherein the surface of the second material is derivatized with an anchoring functionality.  
15
5. The hybrid material of claim 4, wherein the anchoring functionality is selected from the group consisting of vinyl, acrylate, methacrylate, acrylamide, methacrylamide, styrene, divinylbenzene, itaconate, fumarate, alkyne, azo compounds, and combinations thereof.  
20
6. The hybrid material of claim 4, wherein the scaffolding functionality and the anchoring functionality are copolymerizable.
7. The hybrid material of claim 2, wherein the containment vessel is selected from the group consisting of a capillary column, a glass lined steel column, a radial compression column, a trap column, a microfluidic device, a microchip, a sensor, an electronic circuit, a miniaturized SPE device, and an on-column frit.  
25
8. The hybrid material of claim 2, wherein the containment vessel is a fused silica capillary column.  
30



9. The hybrid material of claim 1, wherein the chemical interaction is formation of a covalent bond.
10. The hybrid material of claim 9, wherein the covalent bond is formed by  
5 polymerization.
11. The hybrid material of claim 10, wherein the polymerization is initiated with a radical initiator.
- 10 12. The hybrid material of claim 11, wherein the radical initiator is minimally water soluble.
13. The hybrid material of claim 11, wherein the initiator is selected from the group consisting of 2,2'-azobis(isobutyronitrile), 2,2'-azobis(2-methylpropionamidine)  
15 dihydrochloride, 4,4'-azobis(4-cyanovaleric acid), potassium persulfate, and peracetic acid.
14. The hybrid material of claim 1, wherein the inorganic portion of the hybrid material is a material selected from the group consisting of alumina, silica, titanium  
20 oxide, zirconium oxide, and ceramic material.
15. The hybrid material of claim 1, wherein the inorganic portion of the hybrid material is silica.
- 25 16. The hybrid material of claim 1, wherein the PSN is the product of a reaction of an organosilane and an inorganic silane monomer.
17. The hybrid material of claim 16, wherein the PSN is the product of a reaction of a tetraalkoxysilane and an organosilane containing at least one polymerizable group.

30

18. The hybrid material of claim 17, wherein said tetraalkoxysilane has the formula  $\text{Si}(\text{OR}^1)_4$ , where  $\text{R}^1$  is a  $\text{C}_1 - \text{C}_3$  alkyl moiety.

19. The hybrid material of claim 17, wherein said organosilane is an  
5 organoalkoxysilane having the formula  $\text{R}^2\text{Si}(\text{OR}^1)_3$  or  $\text{R}^6[\text{Si}(\text{OR}^1)_3]_m$  where  $\text{R}^2$  is a styryl, vinyl, an acrylate, methacrylate, acrylamide, methacrylamide, divinylbenzene, itaconate, fumarate, substituted or unsubstituted  $\text{C}_1 - \text{C}_{18}$  alkenylene, alkynylene or  
10 arylene, or a combination thereof;  $\text{R}^1$  is a  $\text{C}_1 - \text{C}_4$  alkyl moiety;  $\text{R}^6$  is a substituted or unsubstituted  $\text{C}_1 - \text{C}_{18}$  alkenylene, alkynylene or arylene moiety bridging two or more  
silicon atoms; and  $m$  is an integer greater than or equal to two.

20. The hybrid material of claim 19 wherein  $\text{R}^2$  is vinyl, methacryloxypropyl, methacrylamidepropyl, or styrylethyl and  $\text{R}^1$  is methyl or ethyl; or  $\text{R}^6$  is a bridging N,N-bis(propylene) acrylamide group,  $m = 2$ , and  $\text{R}^1$  is ethyl or methyl.

15

21. The hybrid material of claim 17, wherein the organosilane is minimally water soluble.

22. The hybrid material of claim 17 wherein said tetraalkoxysilane is selected from  
20 the group consisting of tetramethoxysilane and tetraethoxysilane.

23. The hybrid material of claim 17, wherein the tetraalkoxysilane is tetramethoxysilane.

25 24. The hybrid material of claim 17, wherein the polymerizable group is 3-methacryloxypropyl.

25. The hybrid material of claim 17, wherein the polymerizable group is styrylethyl.

30 26. The hybrid material of claim 17, wherein the tetraalkoxysilane is minimally water soluble.

27. The hybrid material of claim 17, wherein the organosilane is (3-methacryloxypropyl)trimethoxysilane.

28. The hybrid material of claim 1, wherein said pore structure of said hybrid material is modified by further including a surfactant or combination of different surfactants in said reaction, and by subjecting said material to hydrothermal treatment.

29. The hybrid material of claim 28, wherein said surfactant or combination of surfactants are nonionic surfactants.

10

30. The hybrid material of claim 29, wherein the surfactants are selected from the group consisting of surfactants comprised of block copolymers of polyethylene glycol and polypropyleneglycol, surfactants comprised of alkylphenoxypolyethoxyethanol, and polyethyleneglycol.

15

31. The hybrid material of claim 29, wherein the surfactant is Pluronic F38,

32. The hybrid material of claim 28, wherein said surfactant or combination of surfactants are selected from surfactants with a hydrophile-lipophile balance ranging from about 0 to 60.

20

33. The hybrid material of claim 28, wherein said surfactant or combination of surfactants are selected from surfactants with a hydrophile-lipophile balance ranging from about 10 to 50.

25

34. The hybrid material of claim 28, wherein said surfactant or combination of surfactants are selected from surfactants with a hydrophile-lipophile balance ranging from about 20 to 40.

30 35. The hybrid material of claim 28, wherein said surfactant or combination of surfactants are selected from surfactants with a hydrophile-lipophile balance ranging from about 30 to 40.

36. The hybrid material of claim 28, wherein said surfactant or combination of surfactants are selected from surfactants with a hydrophile-lipophile balance is about 33.
- 5 37. The hybrid material of claim 1, wherein said material has been surface modified by a surface modifier selected from the group consisting of an organic group surface modifier, a silanol group surface modifier, a polymeric coating surface modifier, and combinations thereof.
- 10 38. The hybrid material of claim 37, wherein said material has been surface modified by a polymeric coating surface modifier.
39. The hybrid material of claim 37, wherein said material has been surface modified by a combination of an organic group surface modifier and a silanol group surface  
15 modifier.
40. The hybrid material of claim 37, wherein said material has been surface modified by a combination of an organic group surface modifier and a polymeric coating surface  
20 modifier.
41. The hybrid material of claim 37, wherein said material has been surface modified by a combination of a silanol group surface modifier and a polymeric coating surface  
25 modifier.
42. The hybrid material of claim 37, wherein said material has been surface modified by a combination of an organic group surface modifier, a silanol group surface modifier, and a polymeric coating surface modifier.
43. The hybrid material of claim 37, wherein said material has been surface modified  
30 by a silanol group surface modifier.

44. The hybrid material of claim 37, wherein said material has been surface modified via formation of an organic covalent bond between an organic group of the material and a surface modifier.

5 45. The hybrid material of claim 37, wherein the surface modifier has the formula  $Z_a(R')_b\text{Si-R}$ , where  $Z = \text{Cl, Br, I, C}_1 - \text{C}_5 \text{ alkoxy, dialkylamino or trifluoromethanesulfonate}$ ;  $a$  and  $b$  are each an integer from 0 to 3 provided that  $a + b = 3$ ;  $R'$  is a  $\text{C}_1 - \text{C}_6$  straight, cyclic or branched alkyl group, and  $R$  is a functionalizing group.

10

46. The hybrid material of claim 45 wherein  $R'$  is selected from the group consisting of methyl, ethyl, propyl, isopropyl, butyl, t-butyl, sec-butyl, pentyl, isopentyl, hexyl and cyclohexyl.

15 47. The hybrid material of claim 45 wherein said functionalizing group  $R$  is a  $\text{C}_1 - \text{C}_{30}$  alkyl group.

48. The hybrid material of claim 45 wherein said functionalizing group  $R$  is a  $\text{C}_1 - \text{C}_{20}$  alkyl group.

20

49. The hybrid material of claim 45 wherein said surface modifier is selected from the group consisting of octyltrichlorosilane, octadecyltrichlorosilane, octadecyldimethyl-N, N-dimethylaminosilane, octyldimethylchlorosilane, and octadecyldimethylchlorosilane.

25

50. The hybrid material of claim 45, wherein said surface modifier is octadecyldimethyl-N, N-dimethylaminosilane.

30 51. The hybrid material of claim 45, wherein said functionalizing group  $R$  is selected from the group consisting of alkyl, alkenyl, alkynyl, aryl, cyano, amino, diol, nitro, ester, a cation or anion exchange group, an alkyl group containing an embedded polar functionality and an aryl group containing an embedded polar functionality.

52. A hybrid inorganic/organic monolith comprising a polymerized scaffolding nanocomposite (PSN), wherein the nanocomposite contains a scaffolding functionality capable of chemically interacting with a surface of a second material.
- 5
53. The hybrid inorganic/organic monolith of claim 52, wherein the monolith is a capillary monolith.
54. The hybrid inorganic/organic monolith of claim 53, wherein the monolith has improved properties selected from the group consisting of enhanced wall adhesion and increased resistance to shrinkage.
- 10
55. The hybrid inorganic/organic monolith of claim 54, wherein the enhanced wall adhesion is the result of chemical interaction between the scaffolding functionality of the polymer and an anchoring functionality on the surface of the second material.
- 15
56. The hybrid inorganic/organic monolith of claim 52, wherein the second material is a containment vessel.
- 20
57. The hybrid inorganic/organic monolith of claim 52, wherein the scaffolding functionality is selected from the group consisting of vinyl, acrylate, methacrylate, acrylamide, methacrylamide, styrene, divinylbenzene, itaconate, fumarate, alkyne, and combinations thereof.
- 25
58. The hybrid inorganic/organic monolith of claim 52, wherein the surface of the second material is derivatized with an anchoring functionality.
59. The hybrid inorganic/organic monolith of claim 58, wherein the anchoring functionality is selected from the group consisting of vinyl, acrylate, methacrylate, acrylamide, methacrylamide, styrene, divinylbenzene, itaconate, fumarate, alkyne, azo compounds, and combinations thereof.
- 30

60. The hybrid inorganic/organic monolith of claim 58, wherein the scaffolding functionality and the anchoring functionality are copolymerizable.
- 5 61. The hybrid inorganic/organic monolith of claim 56, wherein the containment vessel is selected from the group consisting of a capillary column, a glass lined steel column, a radial compression column, a trap column, a microfluidic device, a microchip, a sensor, a electronic circuit, a miniaturized SPE device, and an on-column frit.
- 10 62. The hybrid inorganic/organic monolith of claim 56, wherein the containment vessel is a fused silica capillary column.
63. The hybrid inorganic/organic monolith of claim 52, wherein the chemical interaction is formation of a covalent bond.
- 15 64. The hybrid inorganic/organic monolith of claim 63, wherein the covalent bond is formed by polymerization.
65. The hybrid inorganic/organic monolith of claim 64, wherein the polymerization is initiated with a radical initiator.
- 20 66. The hybrid inorganic/organic monolith of claim 65, wherein the radical initiator is minimally water soluble.
- 25 67. The hybrid inorganic/organic monolith of claim 65, wherein the initiator is selected from the group consisting of 2,2'-azobis(isobutyronitrile), 2,2'-azobis(2-methylpropionamidine) dihydrochloride, 4,4'-azobis(4-cyanovaleric acid), potassium persulfate, and peracetic acid.
- 30 68. The hybrid inorganic/organic monolith of claim 52, wherein the inorganic portion of the hybrid material is a material selected from the group consisting of alumina, silica, titanium oxide, zirconium oxide, and ceramic material.

69. The hybrid inorganic/organic monolith of claim 52, wherein the inorganic portion of the hybrid material is silica.

70. The hybrid inorganic/organic monolith of claim 52, wherein the PSN is the product of a reaction of an organosilane and an inorganic silane monomer.

71. The hybrid inorganic/organic monolith of claim 70, wherein the PSN is the product of a reaction of a tetraalkoxysilane and an organosilane containing at least one polymerizable group.

10

72. The hybrid inorganic/organic monolith of claim 71, wherein said tetraalkoxysilane has the formula  $\text{Si}(\text{OR}^1)_4$ , where  $\text{R}^1$  is a  $\text{C}_1 - \text{C}_3$  alkyl moiety.

73. The hybrid inorganic/organic monolith of claim 71, wherein said organosilane is an organoalkoxysilane having the formula  $\text{R}^2\text{Si}(\text{OR}^1)_3$  or  $\text{R}^6[\text{Si}(\text{OR}^1)_3]_m$  where  $\text{R}^2$  is a styryl, vinyl, an acrylate, methacrylate, acrylamide, methacrylamide, divinylbenzene, itaconate, fumarate, substituted or unsubstituted  $\text{C}_1 - \text{C}_{18}$  alkenylene, alkynylene or arylene, or a combination thereof;  $\text{R}^1$  is a  $\text{C}_1 - \text{C}_4$  alkyl moiety;  $\text{R}^6$  is a substituted or unsubstituted  $\text{C}_1 - \text{C}_{18}$  alkenylene, alkynylene or arylene moiety bridging two or more silicon atoms; and  $m$  is an integer greater than or equal to two.

15  
20

74. The hybrid inorganic/organic monolith of claim 73 wherein  $\text{R}^2$  is vinyl, methacryloxypropyl, methacrylamidepropyl, or styrylethyl and  $\text{R}^1$  is methyl or ethyl; or  $\text{R}^6$  is a bridging N,N-bis(propylene)acrylamide group,  $m = 2$ , and  $\text{R}^1$  is ethyl or methyl.

25

75. The hybrid inorganic/organic monolith of claim 71, wherein the organosilane is minimally water soluble.

76. The hybrid inorganic/organic monolith of claim 71, wherein said tetraalkoxysilane is selected from the group consisting of tetramethoxysilane and tetraethoxysilane.

30



77. The hybrid inorganic/organic monolith of claim 71, wherein the tetraalkoxysilane is tetramethoxysilane.
78. The hybrid inorganic/organic monolith of claim 71, wherein the polymerizable group is 3-methacryloxypropyl.
79. The hybrid inorganic/organic monolith of claim 71, wherein the polymerizable group is styrylethyl.
80. The hybrid inorganic/organic monolith of claim 71, wherein the tetraalkoxysilane is minimally water soluble.
81. The hybrid inorganic/organic monolith of claim 71, wherein the organosilane is (3-methacryloxypropyl)trimethoxysilane.
82. The hybrid inorganic/organic monolith of claim 52, wherein said pore structure of said hybrid monolith is modified by further including a surfactant or combination of different surfactants in said reaction, and by subjecting said monolith to hydrothermal treatment.
83. The hybrid inorganic/organic monolith of claim 82, wherein said surfactant or combination of surfactants are nonionic surfactants.
84. The hybrid inorganic/organic monolith of claim 82, wherein the surfactants are selected from the group consisting of surfactants comprised of block copolymers of polyethylene glycol and polypropyleneglycol, surfactants comprised of alkylphenoxypolyethoxyethanol, and polyethyleneglycol.
85. The hybrid inorganic/organic monolith of claim 83, wherein the surfactant is Pluronic F38.

86. The hybrid inorganic/organic monolith of claim 82, wherein said surfactant or combination of surfactants are selected from surfactants with a hydrophile-lipophile balance ranging from about 0 to 60.

5 87. The hybrid inorganic/organic monolith of claim 82, wherein said surfactant or combination of surfactants are selected from surfactants with a hydrophile-lipophile balance ranging from about 10 to 50.

10 88. The hybrid inorganic/organic monolith of claim 82, wherein said surfactant or combination of surfactants are selected from surfactants with a hydrophile-lipophile balance ranging from about 20 to 40.

15 89. The hybrid inorganic/organic monolith of claim 82, wherein said surfactant or combination of surfactants are selected from surfactants with a hydrophile-lipophile balance ranging from about 30 to 40.

90. The hybrid inorganic/organic monolith of claim 82, wherein said surfactant or combination of surfactants are selected from surfactants with a hydrophile-lipophile balance is about 33.

20

91. The hybrid inorganic/organic monolith of claim 52, wherein said material has been surface modified by a surface modifier selected from the group consisting of an organic group surface modifier, a silanol group surface modifier, a polymeric coating surface modifier, and combinations thereof.

25

92. The hybrid inorganic/organic monolith of claim 91, wherein said material has been surface modified by a polymeric coating surface modifier.

30 93. The hybrid inorganic/organic monolith of claim 91, wherein said material has been surface modified by a combination of an organic group surface modifier and a silanol group surface modifier.

94. The hybrid inorganic/organic monolith of claim 91, wherein said material have been surface modified by a combination of an organic group surface modifier and a polymeric coating surface modifier.
- 5 95. The hybrid inorganic/organic monolith of claim 91, wherein said material has been surface modified by a combination of a silanol group surface modifier and a polymeric coating surface modifier.
- 10 96. The hybrid inorganic/organic monolith of claim 91, wherein said material has been surface modified by a combination of an organic group surface modifier, a silanol group surface modifier, and a polymeric coating surface modifier.
- 15 97. The hybrid inorganic/organic monolith of claim 91, wherein said material has been surface modified by a silanol group surface modifier.
98. The hybrid inorganic/organic monolith of claim 91, wherein said material has been surface modified via formation of an organic covalent bond between an organic group of the material and a surface modifier.
- 20 99. The hybrid inorganic/organic monolith of claim 91, wherein the surface modifier has the formula  $Z_a(R')_bSi-R$ , where  $Z = Cl, Br, I, C_1 - C_5$  alkoxy, dialkylamino or trifluoromethanesulfonate;  $a$  and  $b$  are each an integer from 0 to 3 provided that  $a + b = 3$ ;  $R'$  is a  $C_1 - C_6$  straight, cyclic or branched alkyl group, and  $R$  is a functionalizing group.
- 25 100. The hybrid inorganic/organic monolith of claim 99 wherein  $R'$  is selected from the group consisting of methyl, ethyl, propyl, isopropyl, butyl, t-butyl, sec-butyl, pentyl, isopentyl, hexyl and cyclohexyl.
- 30 101. The hybrid inorganic/organic monolith of claim 99 wherein said functionalizing group  $R$  is a  $C_1 - C_{30}$  alkyl group.

102. The hybrid inorganic/organic monolith of claim 99 wherein said functionalizing group R is a C<sub>1</sub> – C<sub>20</sub> alkyl group.

103. The hybrid inorganic/organic monolith of claim 99 wherein said surface modifier  
5 is selected from the group consisting of octyltrichlorosilane, octadecyltrichlorosilane, octadecyldimethyl-N, N-dimethylaminosilane, octyldimethylchlorosilane, and octadecyldimethylchlorosilane.

104. The hybrid inorganic/organic monolith of claim 99, wherein said surface  
10 modifier is octadecyldimethyl-N, N-dimethylaminosilane.

105. The hybrid inorganic/organic monolith of claim 99, wherein said functionalizing group R is selected from the group consisting of alkyl, alkenyl, alkynyl, aryl, cyano, amino, diol, nitro, ester, a cation or anion exchange group, or an alkyl or aryl group  
15 containing an embedded polar functionality.

106. A method of preparation of a hybrid inorganic/organic monolith comprising a polymerized scaffolding nanocomposite (PSN), wherein the nanocomposite contains a scaffolding functionality capable of chemically interacting with a surface of a second  
20 material, said method comprising the steps of

- a) forming a sol-gel by the reaction of two or more monomers;
  - b) initiating a polymerization reaction; and
  - c) allowing the monomers to react through a polymerization sol-gel (PSG) reaction,
- 25 thereby preparing the hybrid inorganic/organic monolith.

107. A method of preparation of a hybrid inorganic/organic monolith comprising a polymerized scaffolding nanocomposite (PSN), wherein the nanocomposite contains a scaffolding functionality capable of chemically interacting with a surface of a second  
30 material, said method comprising the steps of

- a) forming a sol-gel by the reaction of two or more monomers;
- b) initiating a polymerization reaction;

c) allowing the monomers to react through a polymerization sol-gel (PSG) reaction; and

d) modifying the pore structure of the material,  
thereby preparing the hybrid inorganic/organic monolith.

5

108. The method of claim 106 or 107, wherein the sol-gel reaction is acid catalyzed.

109. The method of claim 108, wherein the acid is acetic acid.

10 110. The method of claim 106 or 107, wherein the sol-gel reaction is performed at a temperature ranging from about 0 °C to about room temperature.

111. The method of claim 110, wherein the sol-gel reaction is performed at a temperature of about 0 °C.

15

112. The method of claim 110, wherein the sol-gel reaction is performed at room temperature.

20 113. The method of claim 106 and 107, wherein the sol-gel reaction is performed at low pH.

114. The method of claim 113, wherein the sol-gel reaction is performed at about pH 2-3.

25 115. The method of claim 106 or 107, wherein the sol-gel reaction occurs in the presence of urea.

116. The method of claim 106 or 107, wherein the polymerization is initiated with a radical initiator.

30

117. The method of claim 116, wherein the polymerization is initiated with a radical initiator at increased temperature.
118. The method of claim 117, wherein the increased temperature is above room  
5 temperature.
119. The method of claim 118, wherein the increased temperature is about 60-65°C.
120. The method of claim 116, wherein the radical initiator is minimally water  
10 soluble.
121. The method of claim 116, wherein the initiator is selected from the group consisting of 2,2'-azobis(isobutyronitrile), 2,2'-azobis(2-methylpropionamide) dihydrochloride, 4,4'-azobis(4-cyanovaleric acid), potassium persulfate, and peracetic  
15 acid.
122. The method of claim 106 and 107, wherein the PSG reaction is performed at temperature sufficient to achieve simultaneous polymerization and sol gel reactions.
- 20 123. The method of claim 122, wherein the PSG reaction is performed at 65 °C.
124. The method of claim 122, wherein the PSG reaction is performed for an amount of time sufficient to prepare the hybrid inorganic/organic monolith.
- 25 125. The method of claim 106 or 107, wherein the second material is a containment vessel with a surface capable of receiving the PSN material.  
a derivatized with an anchoring functionality.
126. The method of claim 106 or 107, wherein the surface of the second material is  
30 derivatized with an anchoring functionality.

127. The method of claim 126, wherein the scaffolding functionality and the anchoring functionality are copolymerizable.
128. The method of claim 125, where the containment vessel is selected from the group consisting of a capillary column, a glass lined steel column, a radial compression column, a trap column, a microfluidic device, a microchip, a sensor, an electronic circuit, a miniaturized SPE device, and an on-column frit.
129. The method of claim 128, wherein the containment vessel is a capillary column.
130. The method of claim 129, where the containment vessel is a fused silica capillary column.
131. The method of claim 106 or 107, wherein the chemical interaction is formation of a covalent bond.
132. The method of claim 131, wherein the covalent bond is formed by copolymerization.
133. The method of claim 106 or 107, wherein the PSN is the product of a reaction of an organosilane and an inorganic silane monomer.
134. The method of claim 133, wherein the PSN is the product of a reaction of a tetraalkoxysilane and an organosilane containing at least one polymerizable group.
135. The method of claim 134, wherein said tetraalkoxysilane has the formula  $\text{Si}(\text{OR}^1)_4$ , where  $\text{R}^1$  is a  $\text{C}_1 - \text{C}_3$  alkyl moiety.
136. The method of claim 134, wherein said organosilane is an organoalkoxysilane having the formula  $\text{R}^2\text{Si}(\text{OR}^1)_3$  or  $\text{R}^6[\text{Si}(\text{OR}^1)_3]_m$  where  $\text{R}^2$  is a styryl, vinyl, an acrylate, methacrylate, acrylamide, methacrylamide, divinylbenzene, itaconate, fumarate, substituted or unsubstituted  $\text{C}_1 - \text{C}_{18}$  alkenylene, alkynylene or arylene, or a combination

thereof; R<sup>1</sup> is a C<sub>1</sub> - C<sub>4</sub> alkyl moiety; R<sup>6</sup> is a substituted or unsubstituted C<sub>1</sub> - C<sub>18</sub> alkenylene, alkynylene or arylene moiety bridging two or more silicon atoms; and m is an integer greater than or equal to two.

5 137. The method of claim 136 wherein R<sup>2</sup> is vinyl, methacryloxypropyl, methacrylamidepropyl, or styrylethyl and R<sup>1</sup> is methyl or ethyl; or R<sup>6</sup> is a bridging N,N-bis(propylene)acrylamide group, m = 2, and R<sup>1</sup> is ethyl or methyl.

138. The method of claim 133, wherein the organosilane is minimally water soluble.

10

139. The method of claim 134 wherein said tetraalkoxysilane is selected from the group consisting of tetramethoxysilane and tetraethoxysilane.

140. The method of claim 134, wherein the tetraalkoxysilane is tetramethoxysilane.

15

141. The method of claim 134, wherein the polymerizable group is 3-methacryloxypropyl.

142. The method of claim 134, wherein the polymerizable group is styrylethyl.

20

143. The method of claim 134, wherein the tetraalkoxysilane is minimally water soluble.

25 144. The method of claim 134, wherein the organosilane is (3-methacryloxypropyl)trimethoxysilane.

145. The method of claim 133, wherein the organosilane is (3-methacryloxypropyl)trimethoxysilane and the inorganic silane monomer is tetramethoxysilane.

30



146. The method of claim 145, wherein the (3-methacryloxypropyl)trimethoxysilane and the tetramethoxysilane are present in a volume to volume ratio of 1 to 4.

147. The method of claim 106 or 107, wherein said method further comprises surface  
5 modifying said monolith.

148. The method of claim 147, wherein said monolith has been surface modified by a surface modifier selected from the group consisting of an organic group surface modifier, a silanol group surface modifier, a polymeric coating surface modifier, and  
10 combinations thereof.

149. The method of claim 148, wherein said material has been surface modified by a polymeric coating surface modifier.

150. The method of claim 148, wherein said material has been surface modified by a  
15 combination of an organic group surface modifier and a silanol group surface modifier.

151. The method of claim 148, wherein said material have been surface modified by a combination of an organic group surface modifier and a polymeric coating surface  
20 modifier.

152. The method of claim 148, wherein said material has been surface modified by a combination of a silanol group surface modifier and a polymeric coating surface  
25 modifier.

153. The method of claim 148, wherein said material has been surface modified by a combination of an organic group surface modifier, a silanol group surface modifier, and a polymeric coating surface modifier.

154. The method of claim 148, wherein said material has been surface modified by a  
30 silanol group surface modifier.

155. The method of claim 148, wherein said material has been surface modified via formation of an organic covalent bond between an organic group of the material and a surface modifier.

5 156. The method of claim 106 or 107 wherein said pore structure of said monolith is modified by further including a surfactant or combination of different surfactants in said reaction, and by subjecting said monolith to hydrothermal treatment.

10 157. The method of claim 156 wherein said surfactant or combination of surfactants are nonionic surfactants.

158. The method of claim 156 wherein said monolith is modified by further including a surfactant.

15 159. The method of claim 157, wherein the surfactants are selected from the group consisting of surfactants comprised of block copolymers of polyethylene glycol and polypropyleneglycol, surfactants comprised of alkylphenoxypolyethoxyethanol, and polyethyleneglycol.

20 160. The method of claim 157, wherein the surfactant is Pluronic F38,

161. The method of claim 156 wherein said surfactant or combination of surfactants are selected from surfactants with a hydrophile-lipophile balance ranging from about 0 to 60.

25

162. The method of claim 156 wherein said surfactant or combination of surfactants are selected from surfactants with a hydrophile-lipophile balance ranging from about 10 to 50.

30 163. The method of claim 156 wherein said surfactant or combination of surfactants are selected from surfactants with a hydrophile-lipophile balance ranging from about 20 to 40.

164. The method of claim 156 wherein said surfactant or combination of surfactants are selected from surfactants with a hydrophile-lipophile balance ranging from about 30 to 40.

5

165. The method of claim 156 wherein said surfactant or combination of surfactants are selected from surfactants with a hydrophile-lipophile balance is about 33.

166. The method of claim 156, wherein the hydrothermal treatment comprises  
10 subjecting the material to a temperature of 60-200 °C.

167. The method of claim 156, wherein the hydrothermal treatment comprises  
subjecting the material to a temperature of 65-125 °C.

15 168. The method of claim 167, wherein the temperature is 120 °C.

169. The method of claim 158, wherein the pore structure is modified by  
hydrothermal treatment comprising further condensation of the siloxane network formed  
during the PSG reaction, and dissolution and redeposition of silicic acid silicates from  
20 and to the surface of the pore structure.

170. The method of claim 169, wherein the condensation is base catalyzed.

171. The method of claim 170, wherein the base is ammonia.

25

172. The method of claim 171, wherein the ammonia is generated by high temperature  
decomposition of urea.

173. The method of claim 147, wherein the surface modification step includes surface  
30 modifying said monolith with a surface modifier having the formula  $Z_a(R')_bSi-R$ , where  
 $Z = Cl, Br, I, C_1 - C_5$  alkoxy, dialkylamino or trifluoromethanesulfonate; a and b are each

an integer from 0 to 3 provided that  $a + b = 3$ ;  $R'$  is a  $C_1 - C_6$  straight, cyclic or branched alkyl group, and  $R$  is a functionalizing group.

174. The method of claim 173 wherein  $R'$  is selected from the group consisting of methyl, ethyl, propyl, isopropyl, butyl, t-butyl, sec-butyl, pentyl, isopentyl, hexyl and cyclohexyl.

175. The method of claim 173 wherein said functionalizing group  $R$  is a  $C_1 - C_{30}$  alkyl group.

176. The method of claim 173 wherein said functionalizing group  $R$  is a  $C_1 - C_{20}$  alkyl group.

177. The method of claim 173 wherein said functionalizing group  $R$  is a  $C_1 - C_{10}$  alkyl group.

178. The method of claim 173 wherein said surface modifier is selected from the group consisting of octyltrichlorosilane, octadecyltrichlorosilane, octyldimethylchlorosilane, octadecyldimethyl-N,N-dimethylaminosilane, and octadecyldimethylchlorosilane.

179. The method of claim 178 wherein said surface modifier is octadecyldimethyl-N,N-dimethylaminosilane.

180. The method of claim 173, wherein said functionalizing group  $R$  is selected from the group consisting of alkyl, alkenyl, alkynyl, aryl, cyano, amino, diol, nitro, ester, a cation or anion exchange group, or an alkyl or aryl group containing an embedded polar functionality.

181. The method of claim 147 wherein any free silanol groups remaining from said surface modification procedure are endcapped.

182. A separations device comprising

a) a surface capable of accepting a monolith material comprising a polymerized scaffolding nanocomposite (PSN) material, said surface comprising an anchoring functionality and

5 b) a hybrid inorganic/organic monolith comprising a polymerized scaffolding nanocomposite (PSN), wherein the nanocomposite contains a scaffolding functionality capable of chemically interacting with the anchoring functionality on said surface, and wherein said hybrid organic/inorganic monolith is anchored to said surface by a chemical interaction between said scaffolding functionality and anchoring  
10 functionality.

183. The separations device of claim 182, wherein said device is selected from the group consisting of chromatographic columns, thin layer plates, filtration membranes, sample cleanup devices, and microtiter plates.

15

184. The separations device of claim 182, wherein said device is a chromatographic column.

185. The separations device of claim 184, wherein the chromatographic column has an  
20 inner diameter (I.D.) greater than 50  $\mu\text{m}$ .

186. The separations device of claim 184, wherein the chromatographic column has an I.D. greater than of 100  $\mu\text{m}$ .

25 187. The separations device of claim 184, wherein the chromatographic column has an I.D. greater than of 150  $\mu\text{m}$ .

188. The separations device of claim 184, wherein the chromatographic column has an I.D. greater than of 200  $\mu\text{m}$ .

30

189. The separations device of claim 184, wherein the chromatographic column has an I.D. greater than of 250  $\mu\text{m}$ .

190. The separations device of claim 184, wherein said device is a capillary column.

191. The separations device of claim 184 wherein said device is a fused-inorganic  
5 capillary column, wherein the inorganic portion is selected from the group consisting of  
silica, alumina, zirconium oxide, titanium oxide, ceramics, tin oxide, and combinations  
thereof.

192. The separations device of claim 182 wherein the monolith has improved  
10 properties selected from the group consisting of enhanced wall adhesion and increased  
resistance to shrinkage.

193. The separations device of claim 192, wherein the enhanced wall adhesion is the  
result of chemical interaction between the scaffolding functionality of the polymer and  
15 the anchoring functionality of the wall of the containment vessel.

194. A fused-silica capillary column, comprising  
a) a fused-silica capillary column having a cylindrical interior surface  
capable of accepting a monolith comprising a polymerized scaffolding nanocomposite  
20 (PSN) material, said interior surface comprising an anchoring functionality, and  
b) a hybrid inorganic/organic monolith comprising a polymerized  
scaffolding nanocomposite (PSN), wherein the nanocomposite contains a scaffolding  
functionality capable of chemically interacting with the anchoring functionality on said  
surface, and wherein said hybrid organic/inorganic monolith is anchored to said surface  
25 by a chemical interaction between said scaffolding functionality and anchoring  
functionality.

195. The fused-silica capillary column of claim 194, wherein the capillary column has  
an inner diameter (I.D.) greater than 50  $\mu\text{m}$ .

30

196. The fused-silica capillary column of claim 194, wherein the capillary column has  
an I.D. greater than of 100  $\mu\text{m}$ .

197. The fused-silica capillary column of claim 194, wherein the capillary column has an I.D. greater than of 150  $\mu\text{m}$ .

5 198. The fused-silica capillary column of claim 194, wherein the capillary column has an I.D. greater than of 200  $\mu\text{m}$ .

199. The fused-silica capillary column of claim 194, wherein the capillary column has an I.D. greater than of 250  $\mu\text{m}$ .

10

200. The fused-silica capillary column of claim 194, wherein the scaffolding functionality is selected from the group consisting of vinyl, acrylate, methacrylate, acrylamide, methacrylamide, styrene, divinylbenzene, itaconate, fumarate, alkyne, and combinations thereof.

15

201. The fused-silica capillary column of claim 194, wherein the anchoring functionality is selected from the group consisting of vinyl, acrylate, methacrylate, acrylamide, methacrylamide, styrene, divinylbenzene, itaconate, fumarate, alkyne, azo compounds, and combinations thereof.

20

202. The fused-silica capillary column of claim 194, wherein the scaffolding functionality and the anchoring functionality are copolymerizable.

25

203. The fused-silica capillary column of claim 194, wherein the chemical interaction is formation of a covalent bond.

204. The fused-silica capillary column of claim 203, wherein the covalent bond is formed by polymerization.

30

205. The fused-silica capillary column of claim 204, wherein the polymerization is initiated with a radical initiator.

206. The fused-silica capillary column of claim 205, wherein the radical initiator is minimally water soluble.
- 5 207. The fused-silica capillary column of claim 206, wherein the initiator is selected from the group consisting of 2,2'-azobis(isobutyronitrile), 2,2'-azobis(2-methylpropionamidine) dihydrochloride, 4,4'-azobis(4-cyanovaleric acid), potassium persulfate, and peracetic acid.
- 10 208. The fused-silica capillary column of claim 194, wherein the inorganic portion of the hybrid material is a material selected from the group consisting of alumina, silica, titanium oxide, zirconium oxide, and ceramic material.
- 15 209. The fused-silica capillary column of claim 194, wherein the inorganic portion of the hybrid material is silica.
210. The fused-silica capillary column of claim 194, wherein the PSN is the product of a reaction of an organosilane and an inorganic silane monomer.
- 20 211. The fused-silica capillary column of claim 210, wherein the PSN is the product of a reaction of a tetraalkoxysilane and an organosilane containing at least one polymerizable group.
- 25 212. The fused-silica capillary column of claim 211, wherein said tetraalkoxysilane has the formula  $\text{Si}(\text{OR}^1)_4$ , where  $\text{R}^1$  is a  $\text{C}_1 - \text{C}_3$  alkyl moiety.
- 30 213. The fused-silica capillary column of claim 211, wherein said organosilane is an organoalkoxysilane having the formula  $\text{R}^2\text{Si}(\text{OR}^1)_3$  or  $\text{R}^6[\text{Si}(\text{OR}^1)_3]_m$  where  $\text{R}^2$  is a styryl, vinyl, an acrylate, methacrylate, acrylamide, methacrylamide, divinylbenzene, itaconate, fumarate, substituted or unsubstituted  $\text{C}_1 - \text{C}_{18}$  alkenylene, alkynylene or arylene, or a combination thereof;  $\text{R}^1$  is a  $\text{C}_1 - \text{C}_4$  alkyl moiety;  $\text{R}^6$  is a substituted or



unsubstituted C<sub>1</sub> - C<sub>18</sub> alkenylene, alkynylene or arylene moiety bridging two or more silicon atoms; and m is an integer greater than or equal to two.

214. The fused-silica capillary column of claim 213, wherein R<sup>2</sup> is vinyl,  
5 methacryloxypropyl, methacrylamidepropyl, or styrylethyl and R<sup>1</sup> is methyl or ethyl; or R<sup>6</sup> is a bridging N,N-bis(propylene)acrylamide group, m = 2, and R<sup>1</sup> is ethyl or methyl.

215. The fused-silica capillary column of claim 211, wherein the organosilane is minimally water soluble.

10

216. The fused-silica capillary column of claim 211, wherein said tetraalkoxysilane is selected from the group consisting of tetramethoxysilane and tetraethoxysilane.

217. The fused-silica capillary column of claim 211, wherein the tetraalkoxysilane is  
15 tetramethoxysilane.

218. The fused-silica capillary column of claim 211, wherein the polymerizable group is 3-methacryloxypropyl.

20 219. The fused-silica capillary column of claim 211, wherein the polymerizable group is styrylethyl.

220. The fused-silica capillary column of claim 211, wherein the tetraalkoxysilane is minimally water soluble.

25

221. The fused-silica capillary column of claim 211, wherein the organosilane is (3-methacryloxypropyl)trimethoxysilane.

222. The fused-silica capillary column of claim 194, wherein the pore structure of said  
30 hybrid monolith is modified by further including a surfactant or combination of different surfactants in said reaction, and by subjecting said monolith to hydrothermal treatment.

223. The fused-silica capillary column of claim 222, wherein said surfactant or combination of surfactants are nonionic surfactants.

5 224. The fused-silica capillary column of claim 223, wherein the surfactants are selected from the group consisting of surfactants comprised of block copolymers of polyethylene glycol and polypropyleneglycol, surfactants comprised of alkylphenoxypolyethoxyethanol, and polyethyleneglycol.

10 225. The fused-silica capillary column of claim 223, wherein the surfactant is Pluronic F38,

226. The fused-silica capillary column of claim 222, wherein said surfactant or combination of surfactants are selected from surfactants with a hydrophile-lipophile  
15 balance ranging from about 0 to 60.

227. The fused-silica capillary column of claim 222, wherein said surfactant or combination of surfactants are selected from surfactants with a hydrophile-lipophile balance ranging from about 10 to 50.

20

228. The fused-silica capillary column of claim 222, wherein said surfactant or combination of surfactants are selected from surfactants with a hydrophile-lipophile balance ranging from about 20 to 40.

25 229. The fused-silica capillary column of claim 222, wherein said surfactant or combination of surfactants are selected from surfactants with a hydrophile-lipophile balance ranging from about 30 to 40.

30 230. The fused-silica capillary column of claim 222, wherein said surfactant or combination of surfactants are selected from surfactants with a hydrophile-lipophile balance is about 33.

231. The fused-silica capillary column of claim 194, wherein said monolith has been surface modified by a surface modifier selected from the group consisting of an organic group surface modifier, a silanol group surface modifier, a polymeric coating surface modifier, and combinations thereof.

5

232. The fused-silica capillary column of claim 231, wherein said material has been surface modified by a polymeric coating surface modifier.

10

233. The fused-silica capillary column of claim 231, wherein said material has been surface modified by a combination of an organic group surface modifier and a silanol group surface modifier.

15

234. The fused-silica capillary column of claim 231, wherein said material have been surface modified by a combination of an organic group surface modifier and a polymeric coating surface modifier.

20

235. The fused-silica capillary column of claim 231, wherein said material has been surface modified by a combination of a silanol group surface modifier and a polymeric coating surface modifier.

25

236. The fused-silica capillary column of claim 231, wherein said material has been surface modified by a combination of an organic group surface modifier, a silanol group surface modifier, and a polymeric coating surface modifier.

30

237. The fused-silica capillary column of claim 231, wherein said material has been surface modified by a silanol group surface modifier.

238. The fused-silica capillary column of claim 231, wherein said material has been surface modified via formation of an organic covalent bond between an organic group of the material and a surface modifier.

239. The fused-silica capillary column of claim 231, wherein the surface modifier has the formula  $Z_a(R')_bSi-R$ , where  $Z = Cl, Br, I, C_1 - C_5$  alkoxy, dialkylamino or trifluoromethanesulfonate;  $a$  and  $b$  are each an integer from 0 to 3 provided that  $a + b = 3$ ;  $R'$  is a  $C_1 - C_6$  straight, cyclic or branched alkyl group, and  $R$  is a functionalizing group.
240. The fused-silica capillary column of claim 239, wherein  $R'$  is selected from the group consisting of methyl, ethyl, propyl, isopropyl, butyl, t-butyl, sec-butyl, pentyl, isopentyl, hexyl and cyclohexyl.
241. The fused-silica capillary column of claim 239, wherein said functionalizing group  $R$  is a  $C_1 - C_{30}$  alkyl group.
242. The fused-silica capillary column of claim 239, wherein said functionalizing group  $R$  is a  $C_1 - C_{20}$  alkyl group.
243. The fused-silica capillary column of claim 239, wherein said surface modifier is selected from the group consisting of octyltrichlorosilane, octadecyltrichlorosilane, octadecyldimethyl-N, N-dimethylaminosilane, octyldimethylchlorosilane, and octadecyldimethylchlorosilane.
244. The fused-silica capillary column of claim 239, wherein said surface modifier is octadecyldimethyl-N, N-dimethylaminosilane.
245. The fused-silica capillary column of claim 239, wherein said functionalizing group  $R$  is selected from the group consisting of alkyl, alkenyl, alkynyl, aryl, cyano, amino, diol, nitro, ester, a cation or anion exchange group, or an alkyl or aryl group containing an embedded polar functionality.
246. A method of *in situ* preparation of a hybrid inorganic/organic monolith in a fused-silica capillary column, said method comprising:

forming an anchoring functionality on an interior surface of said capillary column; and

forming inside said capillary column a hybrid inorganic/organic monolith comprising a polymerized scaffolding nanocomposite (PSN), wherein the  
5 nanocomposite contains a scaffolding functionality capable of chemically interacting with the anchoring functionality on said surface, said monolith being formed by:

- a) forming a sol-gel by the reaction of two or more monomers;
- b) initiating a polymerization reaction; and
- c) allowing the monomers to react through a polymerization sol-gel (PSG)  
10 reaction;

whereby said scaffolding functionality and said anchoring functionality chemically interact to thereby anchor said monolith to said surface, such that a hybrid inorganic/organic monolith is prepared *in situ* in the fused-silica capillary column.

15 247. A method of *in situ* preparation of a hybrid inorganic/organic monolith in a fused-silica capillary column, said method comprising:

forming an anchoring functionality on an interior surface of said capillary column; and

forming inside said capillary column a hybrid inorganic/organic monolith  
20 comprising a polymerized scaffolding nanocomposite (PSN), wherein the nanocomposite contains a scaffolding functionality capable of chemically interacting with the anchoring functionality on said surface, said monolith being formed by:

- a) forming a sol-gel by the reaction of two or more monomers;
- b) initiating a polymerization reaction;
- c) allowing the monomers to react through a polymerization sol-gel (PSG)  
25 reaction; and

d) modifying the pore structure of the monolith,  
whereby said scaffolding functionality and said anchoring functionality chemically interact to thereby anchor said monolith to said surface, such that a hybrid  
30 inorganic/organic monolith is prepared *in situ* in the fused-silica capillary column.

248. An inorganic/organic hybrid monolith comprising a scaffolding functionality capable of chemically interacting with a surface of a second material, produced by the process of
- a) forming a sol-gel by the reaction of two or more monomers;
  - 5 b) initiating a polymerization reaction; and
  - c) allowing the monomers to react through a polymerization sol-gel (PSG) reaction.
249. An inorganic/organic hybrid monolith comprising a scaffolding functionality capable of chemically interacting with a surface of a second material, produced by the process of
- a) forming a sol-gel by the reaction of two or more monomers;
  - b) initiating a polymerization reaction;
  - c) allowing the monomers to react through a polymerization sol-gel (PSG) reaction; and
  - 15 d) modifying the pore structure of the monolith.
250. A method of preparation of a hybrid inorganic/organic material comprising a polymerized scaffolding nanocomposite (PSN), comprising the steps of
- 20 a) forming a sol-gel by the reaction of two or more monomers;
  - b) initiating a polymerization reaction; and
  - c) allowing the monomers to react through a polymerization sol-gel (PSG) reaction,
- thereby preparing the hybrid inorganic/organic material, wherein the material contains a scaffolding functionality capable of chemically interacting with a surface of a second material.
251. A method of preparation of a hybrid inorganic/organic material comprising a polymerized scaffolding nanocomposite (PSN), comprising the steps of
- 30 a) forming a sol-gel by the reaction of two or more monomers;
  - b) initiating a polymerization reaction;



c) allowing the monomers to react through a polymerization sol-gel (PSG) reaction; and

d) modifying the pore structure of the material,

thereby preparing the hybrid inorganic/organic material, wherein the nanocomposite



5 contains a scaffolding functionality capable of chemically interacting with a surface of a second material.

1/2

*Schematic Description of Monoliths Made by Polymerization Sol-Gel Reactions.***Fig. 1A****Fig. 1B**



2/2

**Fig. 1C****Fig. 1D**

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☒ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**